RUST-OLEUM®
INDUSTRIAL



3100 Rust-O-Cryl



Fast-drying, multi-purpose acrylic resin paint

- Highly versatile
- Rust-inhibitive properties
- Fast-drying
- Suitable as a floor primer

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

3100 Rust-O-Cryl

BESKRIVELSE
RUST-O-CRYL 3100 is a fast-drying, water-based, multi-purpose acrylic resin paint.

ANBEFALET BRUG
Protection and decoration of interior and exterior surfaces. Suitable for use on all porous and non-porous substrates, including plastics, minerals, organic materials and metals. RUST-O-CRYL 3100 contains anti-corrosion pigments and provides rust protection in mildly aggressive environments. RUST-O-CRYL 3100 can also be used as a primer for floors.

TEKNISK DATA

Tæthed:	1.2 – 1.3
Glansgrad ved 60°:	± 20 % at 60°
Faststofindhold i vægt:	52%
Tørstofindhold i volumen:	37%

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	20 minutes
Håndteringstør:	1 hour
Genbehandlingstør:	4 hours (floors: 24 hours)
Fuldt hærdet:	2 days

ANBEFALET VÅDFILMTYKKELSE
100–135 µm depending on application

ANBEFALET TØRFILMTYKKELSE
35–50 µm depending on application

TEORETISK FORBRUG
7-10 m²/L per coat

PRAKTISK FORBRUG
Coverage depends on many factors, such as the roughness or porosity of the surface and product wastage during application.

FORBEHANDLING AF OVERFLADEN
Degrease and remove all dirt using an alkaline cleaner such as Rust-Oleum ND14 Cleaner-Degreaser, or by high-pressure washing with a suitable detergent. Galvanized steel and new aluminum, as well as new concrete, must be etched using Rust-Oleum Surf-Etch 108 Acid Solution. Moss, algae and lichens must be treated with a suitable fungicidal detergent. Remove rust, rust scales and scale, as well as old, non-adhering paint, by sanding or ST3 (ISO 8501-1: 1988) scraping and brushing. Matt down old paint in good condition to remove the gloss. The surface must be clean and dry during application.

BRUGSANVISNING
To ensure perfect uniformity and optimum consistency, the product must be thoroughly mixed before application.

RUST-O-CRYL 3100 must always be applied in two coats.
Metal: For anti-corrosion applications, the minimum dry film thickness per coat is 50 µm. If enhanced protection is required, apply Rust-Oleum 3169 RUST-O-CRYL primer beforehand.
Floors: apply RUST-O-CRYL 3100 as a primer on metal or tiles before applying the Rust-Oleum 7200 Floorcoat PU or 5200 EpoxyShield Ultra topcoats.

ANVENDELSESBETINGELSER
Temperature > 5°C, < 80% RH. The surface temperature must be at least 3°C above the dew point.

PÅFØRING OG FORTYNDING: PENSEL
Do not dilute. Use high-quality brushes designed for water-based paints. When applying with a brush, two coats may be required to achieve the recommended dry film thickness.

PÅFØRING OG FORTYNDING: RULLE
Do not dilute. Use 10 mm woven microfiber rollers. When applying with a roller, two coats may be required to achieve the recommended dry film thickness.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE
Do not dilute.
Nozzle: 0.011 inches / Pressure: 200 bar.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE
Possible, without dilution.

RENGØRING AF UDSTYR/SPILD
Hot water.

BEMÆRKNINGER
RUST-O-CRYL 3100 is not designed to withstand standing water. When applying deep or bright colours (D or TR bases) to a very smooth, non-porous surface, it may take longer to achieve optimum adhesion due to the high concentration of colorants.

SIKKERHEDSDATA

VOC-niveau:	45 g/l
VOC-færdigblanding:	45 g/l
VOC-kategori:	A/i
VOC-grænse:	140 g/l
Bemærkninger om sikkerhed:	Refer to the safety data sheet and the information on the label.

HOLDBARHED
At least 2 years from the date of manufacture (shown on the container) for unopened containers unopened, stored in a dry place in well-ventilated premises, away from direct sunlight, and at at temperatures between 5 and 35°C.

Udstedelsesdato: 24/11/2026

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu