

**RUST-OLEUM®**  
INDUSTRIAL



## COMBIPRIMER® ADHESION PRIMER



# Makes the smoothest surface coatable!

- Easy to apply
- Transparent blue finish
- Recoatable after just 30 minutes
- Very high coverage: 50 m<sup>2</sup>/l

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# COMBIPRIMER® ADHESION PRIMER

## BESKRIVELSE

RUST-OLEUM® CombiPrimer Tack Coat 3302 is an adhesion coat based on a solvent containing acrylic.

## ANBEFALET BRUG

RUST-OLEUM CombiPrimer Tack Coat 3302 should be used on galvanised steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces followed by RUST-OLEUM CombiColor Original or MS. CombiPrimer Tack Coat 3302 is primarily intended for brush application

## TEKNISK DATA

Tæthed: 0,92  
Tørstofindhold i volumen: 20%  
Varmebestandighed: 100°C (dry heat)

## TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør: Remains tacky  
Håndteringstør: Remains tacky  
Genbehandlingstør: After ½ hours but within 24 hours

## ANBEFALET VÅDFILMTYKKELSE

20 µm

## ANBEFALET TØRFILMTYKKELSE

2 µm

## TEORETISK FORBRUG

50 m<sup>2</sup>/l

## PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FORBEHANDLING AF OVERFLADEN

Remove grease, oil and all other surface contaminations by alkaline or high pressure cleaning in combination with appropriate detergents. Remove previous coatings completely. Remove salts, 'white rust', etc., by washing with RUST-OLEUM Surfa-Etch 108 Etching Solution. The surface must be clean and dry during application.

## BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## ANVENDELSESBETINGELSER

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## PÅFØRING OG FORTYNDING: PENSEL

Use natural bristles, longhair brushes.

## RENGØRING AF UDS TYR/SPILD

Use RUST-OLEUM Thinner 160.

## BEMÆRKNINGER

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

## SIKKERHEDSDATA

VOC-niveau: 745 g/l  
VOC-færdigblanding: 745 g/l  
VOC-kategori: A/h  
VOC-grænse: 750 g/l  
Bemærkninger om sikkerhed: Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHED

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 25/10/2021

**Tilgængelige farver og pakningsstørrelser:** Der henvises til den respektive produktside på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

**Ansvarsfraskrivelse:** Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu) eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)