

**RUST-OLEUM®**  
INDUSTRIAL



## 4268 HEAT-RESISTANT PRIMER

# Anti-corrosive heat resistant primer

- Long-term continuous heat resistance up to 425°C
- Contains a high amount of rust inhibitors
- High build primer increases life expectancy of the system
- Excellent flow
- Industrial Quality

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# 4268 HEAT-RESISTANT PRIMER

## DESCRIPTION

Anti-corrosive heat resistant metal primer provides heat resistance up to 425°C dry heat.

## ODPORÚČANÉ POUŽITIE

4268 should be used on new, bare steel or blasted steel surfaces and provides heat resistance up to 425°C dry heat in sheltered or interior environments, if recoated with Heat-Resistant Topcoat 4215. On blasted steel two coats of Primer 4268 should be applied prior to the application of 4215.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,38
Úroveň lesku:	Matt
Trieda korózie:	C3 priemerná ochrana
Obsah pevných látok v objeme:	44,4%
Tepelná odolnosť:	425°C (continuous dry heat)

## DRY TIMES BY 20° C/RH 50%

Na dotyk suché:	30 minutes
Suché na manipuláciu:	2 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdené:	24 hours after minimum service temperature is reached

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

45 µm

## TEORETICKÁ SPOTREBA

9,8 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline- or high pressure (steam) cleaning in combination with appropriate detergents. For optimum results remove rust, rust scale, mill scale and deteriorated coatings by abrasive blasting to Sa 2½ (ISO 8501-1 : 1988), blast profile max. 50 µm. The surface must be clean and dry during application.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Up to 10% volume RUST-OLEUM Thinner 150.  
Use natural bristles, long hair brushes.

## APLIKÁCIA A RIEDENIE: VALEC

Up to 10% volume RUST-OLEUM Thinner 150.  
Use medium nap, polyamide 8 -12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

If required up to 5% volume RUST-OLEUM Thinner 150.  
Pneumatic and electric airless equipment. Tip size: 0.013-0.015 inch. Fluid pressure: 130 - 200 bar.  
Check wet film thickness, avoid excessive film thickness.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

10-20% volume RUST-OLEUM Thinner 150.  
Gravity cup and pressure cup. Tip size: 1.2 -1.8 mm. Atomizing pressure: 2 - 4 bar.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Use RUST-OLEUM Thinner 150/160 or aromatic hydrocarbons.

## POZNÁMKY

Maximum dry film thickness per coat: 60 µm dry, equals 175 µm wet.  
Heat up the coating slowly (max. 50°C/hr) until 150°C.

## SAFETY DATA

Úroveň VOC:	442 g/l
VOC ready mix:	499 g/l
Kategória VOC:	A/i
Limit VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATELNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 03/10/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu