

RUST-OLEUM®
— INDUSTRIAL —



4900 MULTI-SURFACE PU HEAVY-DUTY VARNISH

Clear, water-based, 2 pack polyurethane topcoat



- Available in matt or gloss
- Very abrasion resistant
- Does not yellow; ideal for interior and exterior
- Resists boiling water, alcohol, coffee, red wine and dilute acid and alkalis
- Anti-graffiti; easy to clean with GraffitiShield™ Cleaner

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

4900 MULTI-SURFACE PU HEAVY-DUTY VARNISH

DESCRIPTION

Clear, water-based, 2-component polyurethane topcoat for use on wood (inside), concrete and pre-painted surfaces, also serves as an anti-graffiti coating.

ODPORÚČANÉ POUŽITIE

1. Clear varnish for parquet to protect against stains and scratches
2. Clear sealer for concrete to decrease dusting and increase cleanability
3. As an anti-graffiti coating
4. As a topcoat on previously painted surfaces to provide extra protection and/or change gloss level

TECHNICAL DATA

Hustota (g/cm ³):	1,06
Úroveň lesku:	Gloss, Matt
Úroveň lesku pri 60°:	80% (Gloss)
Úroveň lesku pri 85°:	10% (Matt)
Obsah pevných látok v objeme:	40%
Pomer miešania:	Base : Activator = 2,04 : 0,46 (Volume) = 4 : 1 (Weight)

DRY TIMES BY 20° C/RH 50%

Na dotyk suché:	2 hours
Suché na manipuláciu:	8 hours
Suchý na opätovné natieranie:	4 hours
Úplne vytvrdnuté:	3 days
Život v hrci:	3 hours
Indukčný čas:	5 minutes

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

50 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

20 µm

TEORETICKÁ SPOTREBA

20 m²/l at 20 µm dry film build for vertical surfaces
13,5 m²/l at 30 µm dry film build for horizontal surfaces

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. Porous substrates will increase paint consumption.

PRÍPRAVA POVRCHU

Ensure surface to be varnished is clean, dry, sound and free from wax, oil or any other contamination. If wax has been used clean the surface thoroughly with white spirit prior to sanding. Bare wood should be sanded to a smooth surface, always working with the grain. Sound previously varnished surfaces should be lightly sanded to provide a key. New concrete must be at least 30 days old prior to varnishing plus 1 week per cm if the concrete is above 4 cm thickness.

The moisture content of the substrate may not exceed 4%.

Concrete must be clean, dry and free from any surface laitance (a weak dusty layer on new concrete) and any other surface contaminants such as oils, grease, dirt etc. prior to applying the varnish. Not suitable for direct use on power floated concrete.

NÁVOD NA POUŽITIE

Base and activator are supplied in correct proportions. First stir the base component, then add activator gradually to the base, and mix thoroughly. DO NOT MIX PART UNITS. Wait 5 min after mixing. Do not store mixed product (residue) in a closed can. Badly activated or incorrectly mixed materials will affect performance and may cause early failure or discolouration.

When used outdoors on top of pre-painted surfaces: If the old paint is not UV-resistant, the use of Multi-surface PU Heavy-Duty Varnish is not recommended.

PODMIENKY APLIKÁCIE

Application temperature 10-35°C (at least 3°C above dew point) and RH < 85%.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply evenly using light strokes following the grain of the wood. For best results 3 coats are recommended on new wood/concrete (dilute 1st coat with 10% water) and 2 coats on previously varnished surfaces.

APLIKÁCIA A RIEDENIE: VALEC

Use a short nap mohair roller. For best results 3 coats are recommended on new wood (inside)/concrete (dilute 1st coat with 10% water) and 2 coats on previously varnished surfaces.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Not recommended.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Clean spills with water. When used as an anti-graffiti coating, use GraffitiShield™ Cleaner to remove graffiti.

POZNÁMKY

Not suitable for use on plastic type materials, e.g. imitation wood. Do not wash the varnished surface for at least 3 days after application. If water is spilled on it during this period gently wipe off with a soft dry cloth.

Not suitable for use on bare wood in an outdoor situation.

Taber abrasion: weight loss CS17 / 1000 cycles: 17 mg

Resist stains of: Alcohol (40%), Ammonia, Fatty acids, Coffee, Red Wine, Water, diluted acids & alkalis.

SAFETY DATA

Úroveň VOC:	25 g/l
VOC readymix:	25 g/l
Kategória VOC:	A/j
Limit VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 10/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu