

**RUST-OLEUM**<sup>®</sup>  
INDUSTRIAL



## 5090 ANTI-CONDENSATION

# Prevents dripping from ceiling or walls

- Protects against discontinuous steam or water vapour formation
- Ideal for breweries, kitchens, wash and shower rooms
- 1 Litre product will, after drying, absorb at least 400 grams of water
- Fast drying
- Applicable on slightly damp surfaces

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# 5090 ANTI-CONDENSATION

## DESCRIPTION

Water-based single pack hygienic topcoat protects against discontinuous steam or water vapour formation, in order to prevent condensation and dripping.

## RECOMMENDED USE

5090 should be used on ceilings and the upper parts of walls and is intended for 1 coat, airless application. The product can also be applied by brush or roller, 2 -3 coats, resulting in a textured finish. Can be used where discontinuous steam or water vapour formation occurs, in order to prevent condensation and dripping. 1 Litre product will, after drying, absorb at least 400 grams of water. Old coatings should be humidity resistant. Approvals: absorption by Ceripec.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,22
Gloss Level:	Matt
Solids content in volume:	27%
Heat Resistance:	50 °C (dry heat)

## DRY TIMES BY 20° C/RV 50%

Touch dry:	1 hour (20°C), 6 hours (10°C), 1 hour (30°C)
Dry to handle:	2 hours (20°C), 8 hours (10°C), 2 hours (30°C)
Dry to recoat:	5 hours (20°C), 48 hours (10°C), 4 hours (30°C)
Fully cured:	3 days (20°C), 6 days (10°C), 2 days (30°C)

## RECOMMENDED WET FILM THICKNESS

1000 µm

## RECOMMENDED DRY FILM THICKNESS

270 µm

## THEORETICAL CONSUMPTION

1 m<sup>2</sup>/l

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

New concrete or brick surfaces should cure and dry for at least 30 days prior to application of the coating. Repair surface defects of (coated) concrete or brick surfaces. Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning. Scrape and wire brush carefully to remove deteriorated coatings. Sand previous coatings which are in good condition to remove gloss and to roughen the surface slightly. The surface may be slightly damp during application.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 5°C above dew point.

## APPLICATION & THINNING: BRUSH

Up to 5% volume water. Use a distemper brush.

## APPLICATION & THINNING: ROLLER

Up to 5% volume water. Use a medium nap (10-15 mm), polyamide roller. For textured

surfaces use long nap 14-18 mm rollers.

## APPLICATION & THINNING: AIRLESS SPRAY

If required up to 5% volume water. Pneumatic and electric airless equipment. Tip size: 0.018-0.024 inch (use reverse tips). Fluid pressure: 130 - 200 bar. Check wet film thickness, avoid excessive film thickness.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended.

## CLEANING OF EQUIPMENT / SPILLS

Use water and soap.

## REMARKS

Maximum dry film thickness per coat: 500 µm dry, equals 1850 µm wet. In order to restore absorptive properties, only clean the completely dry surface with cold water and liquid detergent with low pressure, followed by rinsing with plenty of fresh water.

## SAFETY DATA

VOC level:	57 g/l
VOC ready mix:	57 g/l
VOC category:	A/i
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

4 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C. **Keep from freezing.** Freezing will irreversibly affect the product.

Date issued: 12/02/2021

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu