

RUST-OLEUM®
— INDUSTRIAL —



5110 VERTI-PATCH

Light weight repair mortar for walls

- Light weight material does not slump
- Cures as hard as granite; can be drilled after curing
- Does not shrink or crack
- Apply at any depth without the need to build up layers
- Ideal for frost-spalled concrete surfaces with exposed reinforcement

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5110 VERTI-PATCH

BESKRIVELSE

Very strong epoxy repair mortar with special lightweight fillers for repairing damaged vertical concrete, render and stone.

ANBEFALET BRUG

For repair of mineral substrates including repair of frost spalled concrete. (also with exposed reinforcing)

TEKNISK DATA

Tæthed: 1,9
Tørstofindhold i volumen: 98%
Trykstyrke: 28,2 MN/m²

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Genbehandlingstør: 6 hours
Fuldt hærdet: 12 hours
Brugstid: 30 minutes

ANBEFALET VÅDFILMTYKKELSE

2 - 20 mm

ANBEFALET TØRFILMTYKKELSE

2 - 20 mm

TEORETISK FORBRUG

0,6 m² per 2,5 kg at a depth of 5 mm.

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Surfaces should be clean, dry and free of all loose material. Wire brushing or sweeping is generally sufficient. Rust-Oleum ND14 can be used to remove grease and oil. A primer is not usually required if patch or crack repairing. 5401 primer is recommended when applying 5110 Verti-Patch as a thin section screed or on very porous substrates.

BRUGSANVISNING

Each pack (2,5 kg) contains a resinous filler material and 2 containers of curing agent. Mix all the curing agent containers with all the resinous filler. Mix thoroughly. Always mix for a further 5 minutes after the mix appears to be of a uniform colour to ensure thorough dispersion of the curing agent.

ANVENDELSESBETINGELSER

Temperature of material, air and substrate between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

RENGØRING AF UDSKYR/SPILD

Rust-Oleum Thinner 160.

BEMÆRKNINGER

Curing time will be extended by low temperatures. Temperatures of 10°C and below will arrest the curing of the product.

SIKKERHEDSDATA

VOC-niveau: < 10 g/l
grenelle: c
Bemærkninger om sikkerhed: Consult Safety Data Sheet and Safety Information printed on the can. Food products must be removed from the area during application and cure. Please dispose of container with care and in accordance with current regulations.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 10/03/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europas anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu