

RUST-OLEUM®


INDUSTRIAL



5130 DAMP SURFACE PRIMER

Primer for damp floors

- Creates a barrier to stop rising moisture and vapour pressure
- Prevents blistering
- For use on asphalt and concrete
- Very low solvent content
- High build system



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5130 DAMP SURFACE PRIMER

DESCRIPTION

Epoxy primer for damp surfaces prevents air/moisture blistering on concrete and asphalt.

ODPORÚČANÉ POUŽITIE

Suppression of vapor pressure effects to prevent air/moisture blistering on suspect concrete and asphalt balcony surfaces, suspended decking etc.

TECHNICAL DATA

Hustota (g/cm ³):	1,1
Úroveň lesku:	Gloss
Obsah pevných látok v objeme:	96%
Pomer miešania:	Base : Activator = 1,7 : 0,8 (Volume)

DRY TIMES BY 20° C/RH 50%

Na dotyk suché:	6 hours
Suché na manipuláciu:	16 hours
Suchý na opätovné natieranie:	After 16 hours, but within 48 hours
Úplne vytvrdnuté:	2 days
Život v hrnci:	30 minutes

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

250 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

240 µm

TEORETICKÁ SPOTREBA

4m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Ensure surfaces are sound, clean, contaminant-free and as dry as possible before coating. Thoroughly scrub down all dirty surfaces with Rust-Oleum ND 14 (see PDS) alkaline detergent solution followed by thorough rinsing (alternatively steam clean) and dry off. Remove residual contamination by scraping, surface grinding etc. Mechanically remove any unsound/incompatible coatings. Fully grind bare concrete to give an open sandpaper like surface. Reduce undulations/peaks etc by mechanical abrasion or grinding. Remove laitance by acid cleaning and subsequent rinsing. Best results are obtained when blasting the floor. Repair holes or large cracks with Pegacrete or 5180 Epoxy Repair Mortar (see PDS for details).

NÁVOD NA POUŽITIE

Stir thoroughly prior to use. Add the B component (hardener) to the base and stir mechanically. Mix the base to even consistency. Add the activator whilst stirring into the vortex and mix thoroughly, ensuring all activator material is worked away from the sides and the bottom and incorporated (use brush). Transfer the necessary amount to an empty clean, dry plastic can and mix further to ensure thorough blending.

PODMIENKY APLIKÁCIE

Minimum 10°C. Provide air ventilation: open windows and doors.

APLIKÁCIA A RIEDENIE: ŠTETEC

Use undiluted.

APLIKÁCIA A RIEDENIE: VALEC

Do not dilute. Use a 12-15 mm polyamide roller.

APLIKÁCIA A RIEDENIE: HRABLAMI/HRABLIČKOU

Spread out the necessary material over the surface and distribute evenly using a rake or trowel. Use a spike roller if necessary to de-aerate coating.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Rust-Oleum Thinner 160.

POZNÁMKY

Do not apply to inadequately prepared or unsound surfaces. Do not apply as surface temperatures below 10°C or overnight ambient temperatures below 5°C. Low overnight temperatures may further extend minimum overcoating times. Overcoating should be carried out within the timescales above to promote maximum intercoat adhesion and avoid film defects. Ensure surfaces are clean between coats.

SAFETY DATA

Úroveň VOC:	198 g/l
VOC readymix:	198 g/l
Kategória VOC:	A/j
Limit VOC:	350 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 20/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu