

RUST-OLEUM®
— INDUSTRIAL —



5150 SPEED PATCH

Rapid curing concrete repair mortar



- Strong and quick repair of concrete
- Can be recoated within hours
- Does not shrink or crack
- Can be drilled after curing
- Easy all-in-1 packaging, including primer

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5150 SPEED PATCH

BESKRIVELSE

Fast setting, high strength concrete repair mortar provides a durable fast setting repair to frost spalled, eroded and cracked concrete, steps, troughs, ramps, coving etc.

ANBEFALET BRUG

For repair of all damaged mineral and concrete surfaces, including with exposed reinforcing.

TEKNISK DATA

Tæthed: 2,36
Trykstyrke: 42 MN/m²

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Genbehandlingstør: 1 hour
Fuldt hærdet: 1 hour
Brugstid: 10 minutes

ANBEFALET VÅDFILMTYKKELSE

5 - 50 mm

ANBEFALET TØRFILMTYKKELSE

5 - 50 mm

TEORETISK FORBRUG

0,5 m² per 10 kg at a depth of 10 mm.

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

The surface should be reasonably dry, clean and free of loose material. Smooth surfaces should be roughened.

BRUGSANVISNING

Shake the primer bottle before use. The liquid in the larger bottles should be mixed with the dry filler to achieve a dry trowelable mixture.

ANVENDELSESBETINGELSER

Temperature of material, air and substrate between 5 and 30°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING OG FORTYNDING: RIVE/MURSKKE

Prime the surface by brush. Apply the mixed Speed Patch using compression with a trowel to work it into the repair area. Further compression causes the surface to become wetter which makes finishing easier. The mixed components will remain usable for 10-15 minutes according to temperature and volume of material.

RENGØRING AF Udstyr/SPILD

Rust-Oleum Thinner 160.

SIKKERHEDSDATA

VOC-niveau: 0 g/l
grenelle: c
Bemærkninger om sikkerhed: Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C. If stored for long periods, the resin/filler material should be thoroughly mixed prior to addition of the bottles of curing agent.

Udstedelsesdato: 10/03/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europas anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu