

RUST-OLEUM®
— INDUSTRIAL —



5160 FLEXI-JOINT FILLER

Flexible PU filler for expansion joints



- Remains flexible to allow the floor to expand and collapse
- Durable polyurethane product
- Good resistance against oils and chemicals
- Low odour
- For indoor and outdoor use

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5160 FLEXI-JOINT FILLER

BESKRIVELSE

Pourable flexible polyurethane joint filler with excellent chemical resistance for expansion joints.

ANBEFALET BRUG

Repair and filling of expansion and other floor joint areas.

TEKNISK DATA

Tæthed: 1,3
Tørstofindhold i volumen: 99%
Blandingsforhold: Base : Activator = 1,4 : 0,6 (Volume)

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør: 2 hours
Håndteringstør: 12 hours
Genbehandlingstør: Do not recoat
Fuldt hærdet: 7 days
Brugstid: 1 hour

TEORETISK FORBRUG

20 m per 2 litre unit with a joint of 10 mm depth and 10 mm width.

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Ensure the sides of the joint are clean and dry. Any damage joint edges should be repaired with Epoxy Repair Mortar 5180.

BRUGSANVISNING

Mix the 2 components together thoroughly for at least 3 minutes until homogenous.

ANVENDELSES BETINGELSER

Temperature of material, air and substrate between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING OG FORTYNDING: RIVE/MURSKE

For joints 5-10 mm wide, depth should be equal to width. For joints 10-20 mm wide, depth should be 10 mm. For joints over 20 mm wide, depth should be half the width. Product may be poured. To facilitate this, crimp the rim of the tin and pour evenly into the prepared joint, leaving the top of the sealant just below the level of the floor. Remove any remaining air bubbles by running a flat blade across the surface. The Flexi Joint Rod should be used to reduce deeper joints to the desired depth. Use 5401 to improve adhesion.

RENGØRING AF Udstyr/SPILD

Rust-Oleum Thinner 160.

SIKKERHEDSDATA

VOC-niveau: 0 g/l
grenelle: aplus
Bemærkninger om sikkerhed: Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 10/03/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europas anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu