

**RUST-OLEUM®**  
INDUSTRIAL



## 569 QUICK DRYING METAL PRIMER

# Quick drying metal primer

- Recoatable after just 2 hours
- Durable anti-corrosion system in just one day
- Excellent flow
- Tintable in virtually any colour
- Increases life expectancy of the Alkythane topcoat

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# 569 QUICK DRYING METAL PRIMER

## ОПИСАНИЕ

Single pack quick drying metal primer for bare and lightly rusted metal.

## ПРЕПОРЪЧАНА УПОТРЕБА

569/580 should be used on new, blasted or slightly rusted steel surfaces. Depending on the exposure conditions RUST-OLEUM 569/580 can be recoated with a variety of RUST-OLEUM Systems assuring the appropriate protection; e.g. at heavy industrial exposures a two-coat system of 569/580 and 9100; at light industrial exposures Primer 1060/1080 and/or a second coat followed by Alkythane® 7500.

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1,2
Гланцово ниво:	matt
corrosion_class:	c3_average
Съдържание на твърди вещества в обема:	44,8%
heat_resistance:	120°C (dry heat)

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	1 hour
Сух за употреба:	2 hours
Готов за повторно нанасяне:	After 2 hours
Напълно втвърден:	8 days

## МОКЪР СЛОЙ

80 µm

## СУХ СЛОЙ

35 µm

## РАЗХОДНА НОРМА

12,8 m²/l

## КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. For optimum results remove rust, rust scale, mill scale and deteriorated coatings by abrasive blasting to Sa 2½ (ISO 8501-1 : 1988), blast profile max. 50 µm. If blasting is not possible remove loose rust and loose coatings by scraping and/or wire brushing to St 3 (ISO 8501-1 : 1988). Sand previous coatings which are in good condition to remove gloss and to roughen the surface slightly. The surface must be clean and dry during application.

## НАЧИН НА УПОТРЕБА

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Dilute up to 10% volume RUST-OLEUM Thinner 633.

Use natural bristles, long hair brushes. Brush application may require 2 coats to achieve recommended dry film thickness.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Dilute up to 10% volume RUST-OLEUM Thinner 633.

Use medium nap, 8-12 mm. rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

## БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

If required, up to 5% volume RUST-OLEUM Thinner 641.

Pneumatic and electric airless equipment. Tip size: 0.013-0.015 inch. Fluid pressure: 130 - 200 bar.

## ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

10-20% volume RUST-OLEUM Thinner 641.

Gravity cup and pressure cup. Tip size: 1,2 - 1,8 mm. Atomizing pressure: 2 - 4 bar.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Use RUST-OLEUM Thinner 633 or white spirit.

## ЗАБЕЛЕЖКИ

Maximum dry film thickness per coat: 60 µm dry, equals 135 µm wet.

## ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	424 g/l
Готов за употреба ЛОС (VOC Readymix):	497 g/l
Категория ЛОС:	A/i
Ограничение за ЛОС:	500 g/l
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

## СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителя е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu