

RUST-OLEUM®
INDUSTRIAL



6035 METAL PRIMER



Rust-resistant red oxide primer for iron and steel

- Rust-resistant
- For iron and steel
- Also suitable for radiators and heating pipes
- For interior and exterior use

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

6035 METAL PRIMER

DESCRIPTION

Rust-resistant red oxide primer for iron and steel. Also suitable for radiators and heating pipes. For interior and exterior use.

RECOMMENDED USE

Rust-Oleum Red Oxide is a rust-resistant primer based on alkyd resin. Protects iron and steel from rust. Also suitable for metals that heat up, such as radiators and heating pipes.

TECHNICAL DATA

Density (g/cm³): Ongeveer 1,5 g/ml
Solids content in volume: 50%

DRY TIMES BY 20° C/RH 50%

Dry to handle: After 2 hours
Dry to recoat: After 18 hours

RECOMMENDED WET FILM THICKNESS

75 µm

RECOMMENDED DRY FILM THICKNESS

35 µm

THEORETICAL CONSUMPTION

12 m²/litres per layer

PRACTICAL CONSUMPTION

The actual usage is dependent on the nature and structure of the surface and the processing method.

SURFACE PREPARATION

The surface must be sound, clean, dry, and free of dust and grease. With wood frames, round off sharp edges so that you can apply a good coating.

Untreated steel: thoroughly remove any mill scale, grease, rust, and dust. Now apply two layers of Lead-free Red Oxide, then one layer of Primer, and finish with Rust-Oleum Combicolor or Mathys Fassilux.

Treated metal in bad condition: remove all parts that adhere poorly or are loose with a stripper or by burning or scraping, and then treat as 'untreated metal'.

The above systems serve as a general description for most common surfaces. For special applications and/or extensive advice, feel free to contact Rust-Oleum Europe.

DIRECTIONS FOR USE

Stir thoroughly before use. If necessary, thin the first layer with 5% white spirit. Apply two layers using a brush, roller, or spray-gun. Always apply an intermediate Primer before applying a finishing layer on metal.

APPLICATION CONDITIONS

Preferably apply between +8°C and +30°C. Do not apply in bright sunlight, nor when rain threatens.

APPLICATION & THINNING: BRUSH

Use long-haired natural brushes.

CLEANING OF EQUIPMENT / SPILLS

White Spirit or brush cleaner.

REMARKS

General: after use, ensure the packaging is firmly closed. Then turn upside down and then upright again to prevent a skin layer forming.

Remnants: Take this product and its packaging to a collection point for hazardous or special waste.

SAFETY DATA

VOC readymix: 340g/l
Remarks regarding safety: Refer to the associated product safety leaflet and the information on the packaging.

SHELF LIFE

Minimum of twelve months from the date of production when kept in unopened cans, original packaging, stored in a dry, well-ventilated area, and not placed in direct sunlight, at temperatures between 5°C and 25°C.

Date issued: 20/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu