

RUST-OLEUM®
INDUSTRIAL



6040 PRIMER SEALER

**Rust-resistant red oxide primer
for iron and steel**



LE SAVOIR-FAIRE EN PROTECTION™

WWW.RUST-OLEUM.EU

6040 PRIMER SEALER

DESCRIPTION

Rust-resistant red oxide primer for iron and steel. Also suitable for radiators and heating pipes. For interior and exterior use.

UTILISATION RECOMMANDÉE

Rust-Oleum Lead-free red oxide is a rust-resistant primer based on alkyd resin. Protects against iron and steel rusting. It is also suitable as a protective undercoat for wood coming into contact with masonry or concrete.

DONNÉES TECHNIQUES

Densité (g/cm³): Ongeveer 1,34 g/ml
Extrait sec en volume: 50%

TEMPS DE SÉCHAGE À 20°C/HR 50%

Au toucher: 2 hours
Recouvrable: After 18 hours

EPAISSEUR DE FILM SEC RECOMMANDÉE

35 µm

CONSUMMATION THÉORIQUE

12 m²/litres per coat

CONSUMMATION PRATIQUE

The actual usage is dependent on the nature and structure of the surface and the processing method.

PRÉPARATION DE SURFACE

The surface must be load-bearing, clean, dry, and free of dust and grease. With wood frames, round off sharp edges so that you can apply a good coating.

Wood coming into contact with concrete or masonry: degrease, sand lightly, and remove all dust. Then apply two layers of Lead-free Red Oxide.

Untreated iron and steel: thoroughly remove any mill scale, grease, rust, and dust. Now apply two layers of Lead-free Red Oxide, then one layer of Primer, and finish with Rust-Oleum Combicolor or Mathys Fassilux.

Bad paint layers: remove bad parts, then clean with Universol. Now apply two layers of Lead-free Red Oxide, then one layer of Primer, and finish with Rust-Oleum Combicolor or Mathys Fassilux.

The above systems serve as a general description for most common surfaces. For special applications and/or extensive advice, feel free to contact Rust-Oleum Europe.

PRÉCAUTIONS D'UTILISATION

Stir thoroughly before use. If necessary, thin the first layer with 5% white spirit. Apply two layers using a brush, roller or spray gun. Always apply an intermediate Primer before applying a finishing layer on metal.

CONDITIONS D'APPLICATION

Preferably apply between +5°C and +30°C. Do not apply in bright sunlight, nor when rain threatens.

APPLICATION & DILUTION: BROUSSE

Use long-haired natural brushes.
If needed, dilute the product with White Spirit.

NETTOYAGE DU MATERIEL / ECLABOUSSURES

Clean with White spirit or brush cleaner.

REMARQUES

General: after use, ensure the packaging is firmly closed. Then turn upside down and then upright again to prevent a skin layer forming.

Remnants: Take this product and the packaging to a collection point for hazardous or special waste.

DONNÉES DE SÉCURITÉ

COV prêt à l'emploi: 389 g/l
Remarques pour la sécurité: Refer to the associated product safety leaflet and the information on the packaging.

DURÉE DE VIE

Minimum of twelve months from the date of production when kept in unopened cans, original packaging, stored in a dry, well-ventilated area, and not placed in direct sunlight, at temperatures between 5°C and 25°C.

Date d'émission: 20/03/2025

Couleurs et conditionnements disponibles: Reportez-vous à la page produit concernée sur www.rust-oleum.eu pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

Notion de responsabilité: Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur www.rust-oleum.eu ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu