

RUST-OLEUM®
— INDUSTRIAL —



769® DAMP-PROOF RUST PRIMER

Single pack metal primer based on fish oil

- Requires minimal surface preparation
- Penetrates deep into the rust for optimal protection
- Expels moisture & air from the surface
- Can be applied on slightly damp surfaces
- Unique proven formula based on fish oil since 1921

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

769® DAMP-PROOF RUST PRIMER

ОПИСАНИЕ

Single pack rust primer based on a fish oil containing alkyd for direct application on slightly moist or dry metal surfaces. Proven formula since 1921!

ПРЕПОРЪЧАНА УПОТРЕБА

769 is specially developed to be applied on hand tool prepared sound rusted steel surfaces. Can be applied on slightly damp surfaces and provides protection under C4 exposure (ISO 12944) conditions with system:

- 769
- 1060 or 1080
- Alkythane® 7500

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1,33
Гланцово ниво:	mat
Съдържание на твърди вещества в обема:	50%
heat_resistance:	120°C (dry heat)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	4 hours
Сух за употреба:	8 hours
Готов за повторно нанасяне:	After 24 hours
Напълно втвърден:	8 days

МОКЪР СЛОЙ

70 µm

СУХ СЛОЙ

35 µm

РАЗХОДНА НОРМА

14,5 m²/l

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

Remove grease, oil and all other surface contaminations with Rust-Oleum ND14 cleaner or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 2 (ISO 8501-1: 1988), light blast cleaning or sanding. Sand previous coatings, which are in good condition to roughen the surface slightly. The surface must be clean and preferably dry during application.

НАЧИН НА УПОТРЕБА

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

УСЛОВИЯ ЗА НАНАСЯНЕ

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Dilute up to 10% volume RUST-OLEUM Thinner 633.
Use natural bristles, long hair brushes.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Dilute up to 10% volume RUST-OLEUM Thinner 633.
Use medium nap, polyamide 8 -12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

If required, up to 5% volume RUST-OLEUM Thinner 641.
Pneumatic and electric airless equipment. Tip size: 0.013-0.015 inch Fluid pressure: 130 - 200 bar.

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

10-20% volume RUST-OLEUM Thinner 641.
Gravity cup and pressure cup. Tip size: 1.2 -1.8 mm. Atomising pressure: 2 - 4 bar.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Use RUST-OLEUM Thinner 160 or mineral spirits.

ЗАБЕЛЕЖКИ

Maximum dry film thickness per coat: 60 µm dry, equals 120 µm wet.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	375 g/l
Готов за употреба ЛОС (VOC Readymix):	456 g/l
Категория ЛОС:	A/i
Ограничение за ЛОС:	500 g/l
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителя е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu