

**RUST-OLEUM®**  
INDUSTRIAL



## 8798 HYGIENIC PRIMER

# Water-based single pack hygienic primer

- Fast drying and recoatable with 8700
- Offers better protection against contamination than non-hygienic paint
- Water-based paint
- Multiple coatings in one day possible
- Can be applied on damp surfaces

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# 8798 HYGIENIC PRIMER

## BESKRIVELSE

Water-based single pack rapid curing hygienic primer protects (with 8700) against normal humidity and contamination indoors and outdoors. Suitable for walls and ceilings.

## ANBEFALT BRUK

8798 should be used on mineral substrates like concrete, plaster, brickwork and masonry for interior- and exterior applications. 8798 will resist normal humidity and can be applied as a wall primer (diluted up to 30% with water), as a topcoat and can be recoated with 8700 Topcoat.

## TEKNISKE DATA

Tetthet:	1.29
Glansgrad:	Satinert
Tørrestoffinnhold i volum:	35%
Varmebestandig:	90 °C (dry heat)

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	30 min (20°C), 2 h (10°C), 30 min (30°C)
Håndterbar:	2 h (20°C), 4 h (10°C), 1 h (30°C)
Overmalbar:	4 h (20°C), 6 h (10°C), 3 h (30°C)
Herdetid:	3 days (20°C), 5 days (10°C), 2 days (30°C)

## ANBEFALT VÅTFILMTYKKELSE

40 µm

## ANBEFALT TØRRFILMTYKKELSE

115 µm

## TEORETISK FORBRUK

9 m<sup>2</sup>/l

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

Remove grease, oil and all other surface contaminations by alkaline or high pressure- (steam) cleaning in combination with appropriate detergents. New concrete, plaster or brick surfaces should cure and dry for at least 30 days prior to application of the coating. Repair surface defects. Remove contamination with RUST-OLEUM FK111 or ND14. Wash total surface with plenty of fresh/warm water or high pressure- (steam) cleaning in order to remove all remnants of contamination and cleaners. Remove deteriorated coatings by scraping and wire brushing. Sand intact coatings to roughen the surface slightly. The surface must be clean and may be slightly damp during application.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PÅFØRINGSBETINGELSER

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 75%. The substrate temperature must be at least 5°C above dew point.

## PÅFØRING & FORTYNNING: PENSEL

Up to 5 vol. % water. Use brushes based on a mixture of synthetic/natural bristles.

## PÅFØRING & FORTYNNING: RULLE

Up to 5 vol. % water. Use medium nap, 8-12 mm, woven acrylic or polyester rollers. For textured surfaces use long nap 14-18 mm rollers.

## PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

If required 5 vol. % with water. Pneumatic and electric airless equipment. Tip size: 0.017-0.024 inch Fluid pressure: 130 - 200 bar. Check wet film thickness, avoid excessive film thickness.

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Not recommended.

## RENGJØRING AV UTSTYR/SPILL

Immediately after use with water and soap.

## MERKNADER

Maximum dry film thickness per coat: 100 µm dry, equals 285 µm wet. On very porous substrates it is advisable to dilute the first coat up to 30% with water, followed by a second coat.

## SIKKERHETSDATA

VOC nivå:	30 g/l
VOC ferdigblandet:	30 g/l
VOC kategori:	A/g
VOC grense:	50 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C. **Protect from freezing.**

Utstedt dato: 20/03/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)