

**RUST-OLEUM®**  
INDUSTRIAL



## ASPHALT REPAIR



# Immediately pot-hole repair

- Simple to use - no mixing required
- Repairs can be driven over immediately after application
- Ideal for repairs 10 mm – 70 mm
- Coverage approx. 0.5 m<sup>2</sup> per 25 kg at 24 mm thick
- Withstands heavy traffic

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# ASPHALT REPAIR

## BESKRIVELSE

A durable bitumen-based patch repair for use on exterior pot-holed asphalt and concrete based on polished aggregate together with liquid binder based on bitumen plus resins and adhesives. Ideal for potholes in roads, car parks, paths and other bituminous and concrete surfaces.

## ANBEFALT BRUK

Ideal for pot-holes in roadways, vehicle parks, loading docks, paths, airfields etc, on bituminous and concrete surfaces.

## ANBEFALT TØRRFILMTYKKELSE

between 25 and 100 mm

## TEORETISK FORBRUK

At a film thickness of 24 mm 25 kg will cover approximately 0.5m<sup>2</sup>. The product can be applied up to 100mm film thickness.

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

Remove all loose material and surface water, oil etc. Apply the primer with a brush on the prepared surface.

## PÅFØRINGSBETINGELSER

Temperature of air, substrate and coating material between 5 and 25°C. At lower temperatures the product will be tougher and is therefore more difficult to apply.

## PÅFØRING & FORTYNNING: RAKE/MURSKJE

Do not dilute the product.

## HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 25°C.

Utstedt dato: 20/03/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

#### Rust-Oleum Netherlands B.V.

Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

#### Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

#### Rust-Oleum France S.A.S.

38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

#### N.V. Martin Mathys S.A.

Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu