

**RUST-OLEUM®**  
INDUSTRIAL



## ASPHALT RESTORER



# Freshes up discoloured asphalt

- Upgrades drab, grey, stained asphalt and tarmac
- Provides an 'as new' appearance
- Covers old line markings and repairs
- Avoids disruptive and costly re-surfacing

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# ASPHALT RESTORER

## DESCRIZIONE

A one component high quality bitumen based coating with fillers and special flow additives. For refurbishing car parks, driveways and footpaths.

## UTILIZZO CONSIGLIATO

For refurbishing car parks, driveways and footpaths.

## TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto: 30 minutes  
Asciutto da rivestire: 2 - 5 hours  
Completamente indurito: 2 - 5 hours. Rain will delay curing by trapping solvents within the coating.

## CONSUMO TEORICO

5 - 10 m<sup>2</sup> per 5 litres, depending on the surface.

## CONSUMO PRATICO

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

## PREPARAZIONE DELLA SUPERFICIE

Surfaces should be dry and free of any loose material. Moss etc. should be removed by scraping and/or jet washing and the surface left to dry thoroughly.

## ISTRUZIONI PER L'USO

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## CONDIZIONI DI APPLICAZIONE

Do not apply during rainfall. Protect from rain for at least 30 minutes after application.

## APPLICAZIONE E DILUIZIONE: PENNELLO

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

## APPLICAZIONE E DILUIZIONE: RULLO

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

## NOTE

This product is intended as a surface coating. It is not designed to strengthen or repair weak or damaged surfaces. This product is designed for use on bitumen based surfaces. It could soften surfaces which contain coal tar. If in doubt, apply a test area and check after 24 hours that no softening has occurred.

## DATI RELATIVI ALLA SICUREZZA

Livello di COV: 286 g/l  
Soluzione premiscelata COV: 286 g/l  
Categoria COV: A/i  
Limite di COV: 500 g/l  
Note riguardanti la sicurezza: Consult Safety Data Sheet and Safety Information printed on the can.

## SCADENZA

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 25°C.

Data del rilascio: 13/05/2025

**Colori e formati di confezione disponibili:** Si prega di consultare la pagina relativa al prodotto su [www.rust-oleum.eu](http://www.rust-oleum.eu) per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

**Dichiarazione di non responsabilità:** Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da [www.rust-oleum.eu](http://www.rust-oleum.eu) o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu