

RUST-OLEUM®
INDUSTRIAL



ASPHALT RESTORER



Freshes up discoloured asphalt

- Upgrades drab, grey, stained asphalt and tarmac
- Provides an 'as new' appearance
- Covers old line markings and repairs
- Avoids disruptive and costly re-surfacing

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

ASPHALT RESTORER

BESKRIVELSE

A one component high quality bitumen based coating with fillers and special flow additives. For refurbishing car parks, driveways and footpaths.

ANBEFALT BRUK

For refurbishing car parks, driveways and footpaths.

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr: 30 minutes
Overmalbar: 2 - 5 hours
Herdetid: 2 - 5 hours. Rain will delay curing by trapping solvents within the coating.

TEORETISK FORBRUK

5 - 10 m² per 5 litres, depending on the surface.

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

KLARGJØRING AV OVERFLATE

Surfaces should be dry and free of any loose material. Moss etc. should be removed by scraping and/or jet washing and the surface left to dry thoroughly.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Do not apply during rainfall. Protect from rain for at least 30 minutes after application.

PÅFØRING & FORTYNNING: PENSEL

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

PÅFØRING & FORTYNNING: RULLE

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

MERKNADER

This product is intended as a surface coating. It is not designed to strengthen or repair weak or damaged surfaces. This product is designed for use on bitumen based surfaces. It could soften surfaces which contain coal tar. If in doubt, apply a test area and check after 24 hours that no softening has occurred.

SIKKERHETSDATA

VOC nivå: 286 g/l
VOC ferdigblandet: 286 g/l
VOC kategori: A/i
VOC grense: 500 g/l
Merknader angående sikkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 25°C.

Utstedt dato: 20/03/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.

Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.

38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.

Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu