

RUST-OLEUM®
INDUSTRIAL



ASPHALT RESTORER



Freshes up discoloured asphalt

- Upgrades drab, grey, stained asphalt and tarmac
- Provides an 'as new' appearance
- Covers old line markings and repairs
- Avoids disruptive and costly re-surfacing

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

ASPHALT RESTORER

DESCRIPTION

A one component high quality bitumen based coating with fillers and special flow additives. For refurbishing car parks, driveways and footpaths.

ODPORÚČANÉ POUŽITIE

For refurbishing car parks, driveways and footpaths.

DRY TIMES BY 20° C/RH 50%

Na dotyk suché: 30 minutes
Suchý na opätovné natieranie: 2 - 5 hours
Úplne vytvrdnuté: 2 - 5 hours. Rain will delay curing by trapping solvents within the coating.

TEORETICKÁ SPOTREBA

5 - 10 m² per 5 litres, depending on the surface.

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

PRÍPRAVA POVRCHU

Surfaces should be dry and free of any loose material. Moss etc. should be removed by scraping and/or jet washing and the surface left to dry thoroughly.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Do not apply during rainfall. Protect from rain for at least 30 minutes after application.

APLIKÁCIA A RIEDENIE: ŠTETEC

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

APLIKÁCIA A RIEDENIE: VALEC

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

POZNÁMKY

This product is intended as a surface coating. It is not designed to strengthen or repair weak or damaged surfaces. This product is designed for use on bitumen based surfaces. It could soften surfaces which contain coal tar. If in doubt, apply a test area and check after 24 hours that no softening has occurred.

SAFETY DATA

Úroveň VOC: 286 g/l
VOC ready mix: 286 g/l
Kategória VOC: A/i
Limit VOC: 500 g/l
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 25°C.

last_updated: 13/05/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu