

**RUST-OLEUM®**  
INDUSTRIAL



## ASPHALT RESTORER



# Freshes up discoloured asphalt

- Upgrades drab, grey, stained asphalt and tarmac
- Provides an 'as new' appearance
- Covers old line markings and repairs
- Avoids disruptive and costly re-surfacing

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU



# ASPHALT RESTORER

## BESKRIVNING

A one component high quality bitumen based coating with fillers and special flow additives. For refurbishing car parks, driveways and footpaths.

## REKOMMENDERAD ANVÄNDNING

For refurbishing car parks, driveways and footpaths.

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr: 30 minutes  
Torktid: 2 - 5 hours  
Fullt härdad: 2 - 5 hours. Rain will delay curing by trapping solvents within the coating.

## ÅTGÅNG

5 - 10 m<sup>2</sup> per 5 litres, depending on the surface.

## ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

## FÖRBEREDELSE

Surfaces should be dry and free of any loose material. Moss etc. should be removed by scraping and/or jet washing and the surface left to dry thoroughly.

## APPLICERING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICERINGSFÖRHÅLLANDEN

Do not apply during rainfall. Protect from rain for at least 30 minutes after application.

## REDSKAP

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

## APPLICERING OCH SPÄDNING: ROLLER

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

## INFORMATION

This product is intended as a surface coating. It is not designed to strengthen or repair weak or damaged surfaces. This product is designed for use on bitumen based surfaces. It could soften surfaces which contain coal tar. If in doubt, apply a test area and check after 24 hours that no softening has occurred.

## SÄKERHETSDATA

VOC-nivå: 286 g/l  
VOC färdigmix: 286 g/l  
VOC-kategori: A/i  
VOC-gräns: 500 g/l  
Anmärkningar om säkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 25°C.

Utgivningsdatum: 13/05/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)