

**RUST-OLEUM®**  
— INDUSTRIAL —



## B95 FLEXIBLE EPOXY

# Two-pack, flexible high-build epoxy for metal

- High build coating (150 micron), very durable and impact proof
- Excellent corrosion-, wear- and impact-resistance
- Flexible coating moves with the surface, avoiding cracking and peeling
- Resistant against humidity and moisture
- Virtually solvent-free: low odour

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# B95 FLEXIBLE EPOXY

## DESCRIPTION

Two-pack, flexible high-build epoxy for metal. Excellent corrosion-, wear- and impact-resistance.

## ODPORUČANÉ POUŽITIE

B95-Flexible Epoxy is designed for application on concrete, masonry, and hand tool prepared, blasted, primed or galvanized steel. B95 offers appropriate corrosion resistance in severe industrial and coastal exposures; high humidity and moisture conditions. Due to its flexibility, it is especially suitable for concrete and steel floors showing good abrasion- and impact resistance; porous substrates should be primed with 5401 or 5421 Impregnation Primer; very dense substrates, like ceramic tiles, should be primed with Super Adhesive 3333 or 3366. B95 can be applied directly on properly prepared steel or galvanized steel, on itself, on 9170/9180 Primers or Epoxy Rust Primer 9169. This product is also suitable for application on old, reversible coatings such as Chlorinated Rubbers, Vinyls, etc.  
If good U.V. and/or chemical resistance is required Polyurethane Topcoat 9600 should be applied.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,47
Úroveň lesku:	Satin
Trieda korózie:	C4 vysoká ochrana
Obsah pevných látok v hmotnosti:	99%
Obsah pevných látok v objeme:	99%
Tepelná odolnosť:	100°C (dry heat) at elevated temperatures discoloration may occur
Pomer miešania:	1 : 1 (Volume)

## DRY TIMES BY 20° C/RH 50%

Na dotyk suché:	8 hours
Suché na manipuláciu:	12 hours
Suchý na opätovné natieranie:	After 24 hours
Úplne vytvrdnuté:	8 days
Život v hmci:	45 minutes for a 10 L mix at 20°C.
Indukčný čas:	15 minutes

## ODPORUČANÁ HRúbKA MOKRÉHO FILMU

150 µm

## ODPORUČANÁ HRúbKA SUCHÉHO FILMU

150 µm

## TEORETICKÁ SPOTREBA

6,6 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand intact coatings to roughen the surface slightly. Check compatibility, especially when applied on reversible coatings, the application of a test-patch is strongly recommended. The surface must be clean and dry during application.

**Concrete and masonry:** New concrete or masonry should cure and dry for at least 30 days before applying the coating system. Remove laitance, any loose or unsound concrete or deteriorated coatings. Smooth concrete should be roughened. Remove curing compounds.

**Steel:** Remove loose rust, mill scale and deteriorated coatings by hand or power tool cleaning to St 2/3 (ISO 8501-01 : 1988). Large areas may be thorough blast-cleaned to Sa 2 (ISO 8501-01 : 1988), blast profile max. 50 µm.

## NÁVOD NA POUŽITIE

Stir individual components thoroughly before mixing them together. Use the boxing method or use a low speed mixer.

## PODMIENKY APLIKÁCIE

Temperature of air, substrate and coating material between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## APLIKÁCIA A RIEDENIE: ŠTETEC

10 to 15% volume RUST-OLEUM Thinner 160.  
Use natural bristles, long hair brushes. Preferably use disposable brushes.

## APLIKÁCIA A RIEDENIE: VALEC

10 to 15% volume RUST-OLEUM Thinner 160.  
Use medium nap polyamide 16 - 20 mm rollers. Preferably use disposable rollers.  
Roller application requires 2 coats to achieve recommended d.f.t.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

5 to 15% volume RUST-OLEUM Thinner 160.  
Pneumatic and electric airless equipment. Tip size: 0.015-0.025 inch. Fluid pressure: 250 - 300 bar.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Use RUST-OLEUM Thinner 160.

## POZNÁMKY

Maximum dry film thickness per coat: 500 µm dry, equals 505 µm wet.

## SAFETY DATA

Úroveň VOC:	16 g/l
VOC readymix:	130 g/l
Kategória VOC:	A/j
Limit VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATELNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 03/10/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu