

**RUST-OLEUM®**  
— INDUSTRIAL —



## **B95 FLEXIBLE EPOXY**

# **Two-pack, flexible high-build epoxy for metal**

- High build coating (150 micron), very durable and impact proof
- Excellent corrosion-, wear- and impact-resistance
- Flexible coating moves with the surface, avoiding cracking and peeling
- Resistant against humidity and moisture
- Virtually solvent-free: low odour

**KNOW-HOW TO PROTECT™**

**WWW.RUST-OLEUM.EU**

# B95 FLEXIBLE EPOXY

## BESKRIVNING

Two-pack, flexible high-build epoxy for metal. Excellent corrosion-, wear- and impact-resistance.

## REKOMMENDERAD ANVÄNDNING

B95-Flexible Epoxy is designed for application on concrete, masonry, and hand tool prepared, blasted, primed or galvanized steel. B95 offers appropriate corrosion resistance in severe industrial and coastal exposures; high humidity and moisture conditions. Due to its flexibility, it is especially suitable for concrete and steel floors showing good abrasion- and impact resistance; porous substrates should be primed with 5401 or 5421 Impregnation Primer; very dense substrates, like ceramic tiles, should be primed with Super Adhesive 3333 or 3366. B95 can be applied directly on properly prepared steel or galvanized steel, on itself, on 9170/9180 Primers or Epoxy Rust Primer 9169. This product is also suitable for application on old, reversible coatings such as Chlorinated Rubbers, Vinyls, etc.  
If good U.V. and/or chemical resistance is required Polyurethane Topcoat 9600 should be applied.

## TEKNISK DATA

Densitet:	1,47
Glansnivå:	Satin
Korrosionsklass:	C4 hög korrosion
Torrsubstansvikt:	99%
Torrsubstansvolym:	99%
Värmebeständighet:	100°C (dry heat) at elevated temperatures discoloration may occur
Blandningsförhållande:	1 : 1 (Volume)

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	8 hours
Hanteringstorr:	12 hours
Torktid:	After 24 hours
Fullt härdad:	8 days
Brukstid:	45 minutes for a 10 L mix at 20°C.
Induktionstid:	15 minutes

## REKOMMENDERAD VÅTFILMSTJOCKLEK

150 µm

## REKOMMENDERAD TORRFILMSTJOCKLEK

150 µm

## ÅTGÅNG

6,6 m<sup>2</sup>/l

## ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FÖRBEREDELSE

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand intact coatings to roughen the surface slightly. Check compatibility, especially when applied on reversible coatings, the application of a test-patch is strongly recommended. The surface must be clean and dry during application.

**Concrete and masonry:** New concrete or masonry should cure and dry for at least 30 days before applying the coating system. Remove laitance, any loose or unsound concrete or deteriorated coatings. Smooth concrete should be roughened. Remove curing compounds.

**Steel:** Remove loose rust, mill scale and deteriorated coatings by hand or power tool cleaning to St 2/3 (ISO 8501-01 : 1988). Large areas may be thorough blast-cleaned to Sa 2 (ISO 8501-01 : 1988), blast profile max. 50 µm.

## APPLICERING

Stir individual components thoroughly before mixing them together. Use the boxing method or use a low speed mixer.

## APPLICERINGSFÖRHÅLLANDEN

Temperature of air, substrate and coating material between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## REDSKAP

10 to 15% volume RUST-OLEUM Thinner 160.  
Use natural bristles, long hair brushes. Preferably use disposable brushes.

## APPLICERING OCH SPÄDNING: ROLLER

10 to 15% volume RUST-OLEUM Thinner 160.  
Use medium nap polyamide 16 - 20 mm rollers. Preferably use disposable rollers.  
Roller application requires 2 coats to achieve recommended d.f.t.

## APPLICERING OCH SPÄDNING: AIRLESSPRUTA

5 to 15% volume RUST-OLEUM Thinner 160.  
Pneumatic and electric airless equipment. Tip size: 0.015-0.025 inch. Fluid pressure: 250 - 300 bar.

## RENGÖRING AV REDSKAP/SPILL

Use RUST-OLEUM Thinner 160.

## INFORMATION

Maximum dry film thickness per coat: 500 µm dry, equals 505 µm wet.

## SÄKERHETSDATA

VOC-nivå:	16 g/l
VOC färdigmix:	130 g/l
VOC-kategori:	A/j
VOC-gräns:	500 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 03/10/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaper i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu