

**RUST-OLEUM®**  
INDUSTRIAL



## **BIOSAN® AQUA**

# **Water-based hygienic wall paint in any colour**

- Decorative hygienic paint in gloss, satin or mat in almost any colour
- Good flow, filling and hiding power
- For use on masonry, plaster, wood or concrete
- Ideal for schools, dressing rooms, kitchens etc.

**KNOW-HOW TO PROTECT™**

**WWW.RUST-OLEUM.EU**

# BIOSAN® AQUA

## DESCRIPTION

Water-based single pack hygienic topcoat for walls and ceilings where hygiene control is essential, tintable in many colours and different gloss levels.

## RECOMMENDED USE

For the interior and exterior coating of walls and ceilings in low wear areas, where hygiene is important. Rated Class 0 to the UK Building Regulations (BS476 Parts 6&7).

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,2 - 1,4
Gloss Level:	Gloss, Matt, Satin
Solids Content in weight:	50-65 %
Solids content in volume:	35-50 %

## DRY TIMES BY 20° C/RV 50%

Touch dry:	45 minutes
Dry to handle:	1 hour
Fully cured:	2 days

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

Painted substrates: apply directly on old sound paints, glossy paints will be roughed up slightly.

Untreated substrates: On woodwork, apply a coat of Pegaprim (water dilutable) or by preference Fassiprim (solvent based). On masonry, plaster, and concrete: apply a coat of Pegalink first. Good adhering and slightly powdery surfaces have to be impregnated first with Pegafix after high pressure cleaning.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

> 10°C; < 80% H.R.

## APPLICATION & THINNING: BRUSH

Apply with flat brush, do not dilute.

## APPLICATION & THINNING: ROLLER

Apply with dispersion roller. Do not dilute.

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 018 / Pressure: 180 bars. If necessary, dilute with some water.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Dilute with maximum 5% volume water.

## CLEANING OF EQUIPMENT / SPILLS

Water.

## REMARKS

Do not apply in full sun or too hot conditions, to avoid that the product dries too fast and consequently to avoid a decreased flow. The use of Biosan products does not exclude the necessity to clean and disinfect on a normal and regular basis.

## SAFETY DATA

VOC level:	max. 110 g/l
VOC ready mix:	max. 110 g/l
VOC category:	A/i
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 12/02/2021

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)