

**RUST-OLEUM®**

INDUSTRIAL



## COMBICOLOR® ORIGINAL AEROSOLS GLOSS

# One coat system for metal protection, direct to rust



- Primer and topcoat in one
- For application onto rust, bare metal
- Usable down to 5°C

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# COMBICOLOR® ORIGINAL AEROSOLS GLOSS

## DESCRIPTION

COMBICOLOR® Aerosols High Gloss 7300 are based on a urethane modified alkyd. Lead- and chromate-free - contains rust-inhibitive pigments for additional corrosion protection - good hiding properties - high gloss appearance.

## DOPORUČENÉ POUŽITÍ

COMBICOLOR® Aerosols High Gloss 7300 can be applied directly on bare, manually derusted or with COMBICOLOR® Anti-Corrosion Primer 3369/3380 primed steel. COMBICOLOR® Aerosols High Gloss 7300 are intended for small maintenance jobs or for touch-up. COMBICOLOR® Aerosols High Gloss 7300 should be used in light industrial exposures, normal humidity and interior and exterior applications.

## DRY TIMES BY 20° C/RH 50%

Suché na manipulaci: 6 hours  
Suchý nátěr: After 2 hours  
Plně vytvrzené: 7 days

## TEORETICKÁ SPOTŘEBA

2 - 3 m<sup>2</sup> per spray can (400 ml).

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with COMBICOLOR® Adhesion Primer 3302.

## PODMÍNKY POUŽITÍ

For optimum results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

## APLIKACE A ŘEDĚNÍ: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

## POZNÁMKY

Prevent application of too thick layers because this can cause problems with drying and sagging. COMBICOLOR® Aerosols can be applied on 7300 Metal (brush version) within 4 hours or after 72 hours.

## SAFETY DATA

Úroveň těkavých organických

látek: 535 - 540 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 22/06/2026

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu