

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® ORIGINAL AEROSOLS GLOSS

One coat system for metal protection, direct to rust



- Primer and topcoat in one
- For application onto rust, bare metal
- Usable down to 5°C

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ORIGINAL AEROSOLS GLOSS

OMSCHRIJVING

RUST-OLEUM® CombiColor Aerosols High Gloss 7300 are based on a urethane modified alkyl. Lead- and chromate-free - contains rust-inhibitive pigments for additional corrosion protection - good hiding properties - high gloss appearance.

AANBEVOLEN GEBRUIK

RUST-OLEUM CombiColor Aerosols High Gloss 7300 can be applied directly on bare, manually derusted or with CombiColor Primer Anti-Corrosion 3369/3380 primed steel. RUST-OLEUM CombiColor Aerosols High Gloss 7300 are intended for small maintenance jobs or for touch-up. RUST-OLEUM CombiColor Aerosols High Gloss 7300 should be used in light industrial exposures, normal humidity and interior applications.

DROOGTIJDEN BIJ 20° C/RV 50%

Hanteerbaar:	6 hours
Overschilderbaar:	After 2 hours
Volledig uitgehard:	7 days

THEORETISCH VERBRUIK

2 - 3 m² per spray can (400 ml).

PRAKTISCH VERBRUIK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ONDERGROND VOORBEHANDELING

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with CombiColor Adhesion Primer 3302.

APPLICATIEOMSTANDIGHEDEN

For optimum results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

VERDUNNING & APPLICATIE: SPUITBUS

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

OPMERKINGEN

Prevent application of too thick layers because this can cause problems with drying and sagging. CombiColor Aerosols can be applied on 7300 Metal (brush version) within 4 hours or after 72 hours.

VEILIGHEIDSGEGEVENS

VOC gehalte:	535 - 540 g/l
Opmerkingen mbt veiligheid:	Consult Safety Data Sheet and Safety Information printed on the can.

HOUDBAARHEID

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Uitgiftedatum: 10/07/2025

Beschikbare kleuren en verpakkingsformaten: Raadpleeg de betreffende productpagina op www.rust-oleum.eu voor een overzicht van de actueel beschikbare kleuren en verpakkingsgrootten.

Disclaimer: De informatie in dit document is naar ons beste weten juist en wordt te goeder trouw, maar zonder garantie gegeven. De gebruiker wordt geacht onafhankelijk de geschiktheid van onze producten voor zijn/haar eigen specifieke toepassing te testen. In geen geval is Rust-Oleum Europe aansprakelijk voor directe of indirecte schade. Producten dienen te worden opgeslagen, behandeld en aangebracht volgens de aanbevelingen van Rust-Oleum Europe op het productinformatieblad (technische fiche). Het is de verantwoordelijkheid van de gebruiker om altijd de laatste versie van het productinformatieblad (technische fiche) te raadplegen en te respecteren. Deze bladen zijn gratis te downloaden van de website www.rust-oleum.eu of op aanvraag bij de afdeling Customer Service (Verkoop binnendienst). Rust-Oleum Europe houdt zich het recht voor om de eigenschappen van haar producten te wijzigen zonder voorafgaande kennisgeving.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu