

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® HAMMERTONE AEROSOL

One coat system for metal protection, direct to rust



- Lead- and chromate-free
- Contains rust-inhibitive pigments for additional corrosion protection
- Excellent hiding properties
- High gloss appearance

LE SAVOIR-FAIRE EN PROTECTION™

WWW.RUST-OLEUM.EU

COMBICOLOR® HAMMERTONE AEROSOL

DESCRIPTION

RUST-OLEUM® CombiColor Aerosols Hammertone 7300 are based on a urethane modified alkylid.

UTILISATION RECOMMANDÉE

RUST-OLEUM CombiColor Aerosols Hammertone 7300 can be applied directly on bare, manually derusted or with CombiPrimer Anti-Corrosion 3369/3380 primed steel. RUST-OLEUM CombiColor Aerosols Hammertone 7300 are intended for small maintenance jobs or for touch-up. RUST-OLEUM CombiColor Aerosols Hammertone 7300 should be used in light industrial exposures, normal humidity and interior applications.

DONNÉES TECHNIQUES

Densité (g/cm³): 1.0 kg/l
Extrait sec en volume: 41.5%
Résistance à la chaleur: 90°C

TEMPS DE SÉCHAGE À 20°C/HR 50%

Manipulable: 4 hours
Recouvrable: 2 hours
Dur à cœur: 7 days

CONSUMMATION THÉORIQUE

2 - 3 m² per spray can (400 ml).

CONSUMMATION PRATIQUE

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÉPARATION DE SURFACE

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application. Galvanized, Zinc and Aluminium surfaces have to be primed first with CombiColor Adhesion Primer 3302.

PRÉCAUTIONS D'UTILISATION

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve

CONDITIONS D'APPLICATION

For optimum results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

REMARQUES

Prevent application of too thick layers because this can cause problems with drying and sagging.

DONNÉES DE SÉCURITÉ

COV prêt à l'emploi: 495 g/l
Catégorie COV: A/i
Limite COV: 500 g/l
Remarques pour la sécurité: Consult Safety Data Sheet and Safety Information printed on the can

DURÉE DE VIE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date d'émission: 10/07/2025

Couleurs et conditionnements disponibles: Reportez-vous à la page produit concernée sur www.rust-oleum.eu pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

Notion de responsabilité: Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur www.rust-oleum.eu ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu