

RUST-OLEUM®

INDUSTRIAL



COMBICOLOR® ORIGINAL AEROSOL WROUGHT IRON

One coat system for metal protection, direct to rust



- Primer and topcoat in one
- For application onto rust, bare metal
- Usable down to 5°C

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ORIGINAL AEROSOL WROUGHT IRON

BESKRIVNING

RUST-OLEUM® CombiColor Aerosol Wrought Iron 7300 is primer and topcoat in one, based on a urethane modified alkyd, providing good drying properties at low temperatures. The product contains rust-inhibitive pigments and is lead- and chromate free.

REKOMMENDERAD ANVÄNDNING

RUST-OLEUM® CombiColor Aerosol Wrought Iron 7300 should be applied on bare, manually derusted or with CombiColor Primer Anti-Corrosion 3369/3380 primed steel. RUST-OLEUM CombiColor Aerosol Wrought Iron 7300 offers corrosion protection in a light industrial environment. For metal structures in a more aggressive industrial environment, prior application of a RUSTOLEUM® CombiColor Primer Anti-Corrosion 3369/3380 is recommended.

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Hanteringstorr: 6 hours
Torktid: After 2 hours
Fullt härdad: 7 days

ÅTGÅNG

2 - 3 m² per spray can (400 ml).

ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FÖRBEREDELSE

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with CombiColor Adhesion Primer 3302.

APPLICERINGSFÖRHÅLLANDEN

For optimum results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

APPLICERING OCH SPÄDNING: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

INFORMATION

Prevent application of too thick layers because this can cause problems with drying and sagging. CombiColor Aerosols can be applied on 7300 Metal (brush version) within 4 hours or after 72 hours.

SÄKERHETSDATA

VOC-nivå: 535 - 540 g/l
Anmärkningar om säkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 22/06/2026

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaper i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu