

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® ADHESION PRIMER AEROSOL

Makes the smoothest surface coatable!



- Easy to apply
- Transparent blue finish
- Recoatable after just 30 minutes
- Very high coverage: 4,4 m²/can

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ADHESION PRIMER AEROSOL

BESKRIVELSE

RUST-OLEUM® CombiColor Aerosol Tack Coat 3302 is an adhesion coat based on a solvent containing acrylic.

ANBEFALT BRUK

RUST-OLEUM CombiColor Aerosol Adhesion Primer 3302 should be used on galvanized steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces followed by RUST-OLEUM CombiColor Aerosols 7300 Topcoats/ Hammered. RUST-OLEUM CombiColor Aerosol Adhesion Primer 3302 is intended for small maintenance jobs. RUST-OLEUM CombiColor Aerosol Adhesion Primer 3302 should be used in light industrial exposures, normal humidity and interior applications.

TEKNISKE DATA

Densitet: 0.87
Tørrestoffinnhold i volum: 7%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr: Remains tacky
Håndterbar: Remains tacky
Tørketid: After 30 minutes but within 24 hours

FORBRUK

4.4 m² per spray can (400 ml)

FORBRUK INFORMASJON

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEREDELSE

Remove dirt, grease, oil and all other surface contaminants by appropriate means or use RUST-OLEUM Alkaline Cleaner/Degreaser ND14. Remove previous coatings completely e.g. with RUST-OLEUM Paint Stripper. The surface must be clean and dry during application.

PÅFØRING

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can at least 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a single, thin layer and avoid application of thick layers. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

PÅFØRINGSBETINGELSER

For optimum results the relative humidity shall be below 85% and the temperature of the can above 0°C.

PÅFØRING & FORTYNNING: PENSEL

Use natural bristles, longhair brushes.

RENGJØRING AV REDSKAP/SØL

Use RUST-OLEUM Thinner 160.

INFORMASJON

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

SIKKERHETSDATA

VOC nivå: 730 g/l
VOC kategori: A/h
VOC grense: 750 g/l
Merknader angående sikkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 22/06/2026

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Forbehold: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu