

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® ANTI-RUST PRIMER AEROSOL

The anti-rust primer in aerosol



- Recoatable within 1 hour or after 48 hours
- For new / slightly rusted surfaces
- Grey for light coloured topcoats
- Red for dark coloured topcoats

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ANTI-RUST PRIMER AEROSOL

ОПИСАНИЕ

RUST-OLEUM® CombiColor Aerosol Anticorrosion 3369/3380 are fast drying primers based on a short oil soya alkylid. The products contain rust-inhibitive pigments and are lead- and chromate free.

ПРЕПОРЪЧАНА УПОТРЕБА

RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 should be used on new, bare or slightly rusted steel surfaces. RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 are intended to be applied on small areas or for touch-up. RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 should be used in light industrial exposures, normal humidity and interior applications and should be recoated with RUSTOLEUM CombiColor Aerosols 7300 Topcoats/Hammered.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1,21
Гланцово ниво:	Мат
Съдържание на твърди вещества в обема:	44,8%
Топлинна устойчивост:	100°C (dry heat)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	15 minutes
Сух за употреба:	30 minutes
Готов за повторно нанасяне:	Within 1 hour or after 48 hours
Напълно втвърден:	7 days

МОКЪР СЛОЙ

80 µm

СУХ СЛОЙ

25 µm

РАЗХОДНА НОРМА

2 m² per spray can at 25 µm dry (400 ml).

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

Remove dirt, grease, oil, and all other surface contaminants by Rust-Oleum Alkaline Cleaner/Degreaser ND14. Remove loose rust and loose coatings. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

НАЧИН НА УПОТРЕБА

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

УСЛОВИЯ ЗА НАНАСЯНЕ

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Up to 10% volume RUST-OLEUM Thinner 7301. Use natural bristles, longhair brushes.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Up to 10% volume RUST-OLEUM Thinner 7301. Use medium nap, 8-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

10-20% volume RUST-OLEUM Thinner 7301. Gravity cup and pressure cup. Tip size: 1.2 - 1.8 mm. Atomizing pressure: 2 - 4 bar.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Use RUST-OLEUM Thinner 7301 or white spirit.

ЗАБЕЛЕЖКИ

Being lead- and chromate free these products do not evolve the risk of toxic fumes when surfaces coated with these products are welded at a later date.

ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	635 g/l
Готов за употреба ЛОС (VOC Readymix):	490 g/l
Категория ЛОС:	A/i
Ограничение за ЛОС:	424 g/l
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 08/07/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu