

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® ANTI-RUST PRIMER AEROSOL

The anti-rust primer in aerosol



- Recoatable within 1 hour or after 48 hours
- For new / slightly rusted surfaces
- Grey for light coloured topcoats
- Red for dark coloured topcoats

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ANTI-RUST PRIMER AEROSOL

BESKRIVELSE

RUST-OLEUM® CombiColor Aerosol Anticorrosion 3369/3380 are fast drying primers based on a short oil soya alkylid. The products contain rust-inhibitive pigments and are lead- and chromate free.

ANBEFALET BRUG

RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 should be used on new, bare or slightly rusted steel surfaces. RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 are intended to be applied on small areas or for touch-up. RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 should be used in light industrial exposures, normal humidity and interior applications and should be recoated with RUSTOLEUM CombiColor Aerosols 7300 Topcoats/Hammered.

TEKNISK DATA

Tæthed:	1,21
Glansgrad:	Mat
Tørstofindhold i volumen:	44,8%
Varmebestandighed:	100°C (dry heat)

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	15 minutes
Håndteringstør:	30 minutes
Genbehandlingstør:	Within 1 hour or after 48 hours
Fuldt hærdet:	7 days

ANBEFALET VÅDFILMTYKKELSE

80 µm

ANBEFALET TØRFILMTYKKELSE

25 µm

TEORETISK FORBRUG

2 m² per spray can at 25 µm dry (400 ml).

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Remove dirt, grease, oil, and all other surface contaminants by Rust-Oleum Alkaline Cleaner/Degreaser ND14. Remove loose rust and loose coatings. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

BRUGSANVISNING

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

ANVENDELSESBETINGELSER

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

PÅFØRING OG FORTYNDING: PENSEL

Up to 10% volume RUST-OLEUM Thinner 7301. Use natural bristles, longhair brushes.

PÅFØRING OG FORTYNDING: RULLE

Up to 10% volume RUST-OLEUM Thinner 7301. Use medium nap, 8-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

10-20% volume RUST-OLEUM Thinner 7301. Gravity cup and pressure cup. Tip size: 1.2 - 1.8 mm. Atomizing pressure: 2 - 4 bar.

RENGØRING AF UDSTYR/SPILD

Use RUST-OLEUM Thinner 7301 or white spirit.

BEMÆRKNINGER

Being lead- and chromate free these products do not evolve the risk of toxic fumes when surfaces coated with these products are welded at a later date.

SIKKERHEDSDATA

VOC-niveau:	635 g/l
VOC-færdigblanding:	490 g/l
VOC-kategori:	A/i
VOC-grænse:	424 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 08/07/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu