

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® ANTI-RUST PRIMER AEROSOL

The anti-rust primer in aerosol



- Recoatable within 1 hour or after 48 hours
- For new / slightly rusted surfaces
- Grey for light coloured topcoats
- Red for dark coloured topcoats

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ANTI-RUST PRIMER AEROSOL

BESCHREIBUNG

RUST-OLEUM® CombiColor Aerosol Anticorrosion 3369/3380 are fast drying primers based on a short oil soya alkylid. The products contain rust-inhibitive pigments and are lead- and chromate free.

EMPFOHLENE VERWENDUNG

RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 should be used on new, bare or slightly rusted steel surfaces. RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 are intended to be applied on small areas or for touch-up. RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 should be used in light industrial exposures, normal humidity and interior applications and should be recoated with RUSTOLEUM CombiColor Aerosols 7300 Topcoats/Hammered.

TECHNISCHE DATEN

Dichte (g/cm ³):	1,21
Glanzgrad:	Matt
Feststoffgehalt in Volume:	44,8%
Hitzebeständigkeit:	100°C (dry heat)

TROCKENZEITEN BEI 20°C/RF 50%

Klebfrei:	15 minutes
Griffest:	30 minutes
Überstreichbar:	Within 1 hour or after 48 hours
Durchgehärtet:	7 days

EMPFOHLENE NASSE SCHICHTDICKE

80 µm

EMPFOHLENE TROCKENSCHICHTDICKE

25 µm

THEORETISCHE ERGIEBIGKEIT

2 m² per spray can at 25 µm dry (400 ml).

PRAKTISCHE ERGIEBIGKEIT

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

UNTERGRUNDVORBEREITUNG

Remove dirt, grease, oil, and all other surface contaminants by Rust-Oleum Alkaline Cleaner/Degreaser ND14. Remove loose rust and loose coatings. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

HINWEISE ZUR VERARBEITUNG

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

ANWENDUNGSBEDINGUNGEN

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

VERDÜNNUNG & ANWENDUNG: PINSEL

Up to 10% volume RUST-OLEUM Thinner 7301. Use natural bristles, longhair brushes.

VERDÜNNUNG & ANWENDUNG: ROLLER

Up to 10% volume RUST-OLEUM Thinner 7301. Use medium nap, 8-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

VERDÜNNUNG & ANWENDUNG: DRUCKLUFTSPRITZ

10-20% volume RUST-OLEUM Thinner 7301. Gravity cup and pressure cup. Tip size: 1.2 - 1.8 mm. Atomizing pressure: 2 - 4 bar.

REINIGUNG DER ARBEITSGERÄTE / SPRITZER

Use RUST-OLEUM Thinner 7301 or white spirit.

BEMERKUNGEN

Being lead- and chromate free these products do not evolve the risk of toxic fumes when surfaces coated with these products are welded at a later date.

SICHERHEITSDATEN

VOC-Gehalt:	635 g/l
VOC-Gehalt Fertigmischung:	490 g/l
VOC-Kategorie:	A/i
VOC-Grenzwert:	424 g/l
Bemerkungen für Sicherheit:	Consult Safety Data Sheet and Safety Information printed on the can.

LAGERFÄHIGKEIT

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Ausgabedatum: 08/07/2025

Verfügbare Farben und Packungsgrößen: Bitte beziehen Sie sich auf die jeweilige Produktseite auf www.rust-oleum.eu für eine Übersicht der aktuell verfügbaren Farben und Größen verpacken.

Haftungsausschluss: Die hierin enthaltenen Informationen wurden nach bestem Wissen wahrheitsgetreu und präzise und im guten Glauben zusammengestellt. Wir übernehmen aber keine Haftung. Wir gehen davon aus, dass sich der Anwender eigenverantwortlich über die Eignung unserer Produkte für seine individuelle Zweckbestimmung informiert hat. Rust-Oleum Europe übernimmt keinerlei Haftung für Folgeschäden oder mittelbare Schäden. Die Produkte müssen gelagert, gehandhabt und unter Bedingungen verwendet werden, die den Empfehlungen von Rust-Oleum Europe entsprechen, die in der neuesten Ausgabe des Produktdatenblatts angegeben sind. Der Anwender muss sicherstellen, dass er die neueste Ausgabe besitzt. Die neuesten Ausgaben des Produktdatenblatts können kostenlos auf www.rust-oleum.eu heruntergeladen oder bei unserer Kundendienstabteilung angefordert werden. Rust-Oleum Europe behält sich das Recht vor, die Eigenschaften seiner Produkte ohne vorherige Ankündigung zu ändern.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu