

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® ANTI-RUST PRIMER AEROSOL

The anti-rust primer in aerosol



- Recoatable within 1 hour or after 48 hours
- For new / slightly rusted surfaces
- Grey for light coloured topcoats
- Red for dark coloured topcoats

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ANTI-RUST PRIMER AEROSOL

OMSCHRIJVING

RUST-OLEUM® CombiColor Aerosol Anticorrosion 3369/3380 are fast drying primers based on a short oil soya alkylid. The products contain rust-inhibitive pigments and are lead- and chromate free.

AANBEVOLEN GEBRUIK

RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 should be used on new, bare or slightly rusted steel surfaces. RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 are intended to be applied on small areas or for touch-up. RUST-OLEUM CombiColor Aerosol Anti-Corrosion Primer 3369/3380 should be used in light industrial exposures, normal humidity and interior applications and should be recoated with RUSTOLEUM CombiColor Aerosols 7300 Topcoats/Hammered.

TECHNISCHE GEGEVENS

Dichtheid (g/cm³):	1,21
Glansgraad:	Mat
Vaste stof gehalte in volume:	44,8%
Hittebestendigheid:	100°C (dry heat)

DROOGTIJDEN BIJ 20° C/RV 50%

Kleefvrij:	15 minutes
Hanteerbaar:	30 minutes
Overschilderbaar:	Within 1 hour or after 48 hours
Volledig uitgehard:	7 days

AANBEVOLEN NATTE LAAGDIKTE

80 µm

AANBEVOLEN DROGE LAAGDIKTE

25 µm

THEORETISCH VERBRUIK

2 m² per spray can at 25 µm dry (400 ml).

PRAKTISCH VERBRUIK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ONDERGROND VOORBEHANDELING

Remove dirt, grease, oil, and all other surface contaminants by Rust-Oleum Alkaline Cleaner/Degreaser ND14. Remove loose rust and loose coatings. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

INSTRUCTIES VOOR GEBRUIK

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

APPLICATIEOMSTANDIGHEDEN

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

VERDUNNING & APPLICATIE: KWAST

Up to 10% volume RUST-OLEUM Thinner 7301. Use natural bristles, longhair brushes.

VERDUNNING & APPLICATIE: ROLLER

Up to 10% volume RUST-OLEUM Thinner 7301. Use medium nap, 8-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

VERDUNNING & APPLICATIE: LUCHTSPUIT

10-20% volume RUST-OLEUM Thinner 7301. Gravity cup and pressure cup. Tip size: 1.2 - 1.8 mm. Atomizing pressure: 2 - 4 bar.

REINIGEN VAN APPARATUUR / SPATTEN

Use RUST-OLEUM Thinner 7301 or white spirit.

OPMERKINGEN

Being lead- and chromate free these products do not evolve the risk of toxic fumes when surfaces coated with these products are welded at a later date.

VEILIGHEIDSGEGEVENS

VOC gehalte:	635 g/l
VOC readymix:	490 g/l
VOC categorie:	A/i
VOC limiet:	424 g/l
Opmerkingen mbt veiligheid:	Consult Safety Data Sheet and Safety Information printed on the can.

HOUDBAARHEID

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Uitgiftedatum: 08/07/2025

Beschikbare kleuren en verpakkingsformaten: Raadpleeg de betreffende productpagina op www.rust-oleum.eu voor een overzicht van de actueel beschikbare kleuren en verpakkingsgrootten.

Disclaimer: De informatie in dit document is naar ons beste weten juist en wordt te goeder trouw, maar zonder garantie gegeven. De gebruiker wordt geacht onafhankelijk de geschiktheid van onze producten voor zijn/haar eigen specifieke toepassing te testen. In geen geval is Rust-Oleum Europe aansprakelijk voor directe of indirecte schade. Producten dienen te worden opgeslagen, behandeld en aangebracht volgens de aanbevelingen van Rust-Oleum Europe op het productinformatieblad (technische fiche). Het is de verantwoordelijkheid van de gebruiker om altijd de laatste versie van het productinformatieblad (technische fiche) te raadplegen en te respecteren. Deze bladen zijn gratis te downloaden van de website www.rust-oleum.eu of op aanvraag bij de afdeling Customer Service (Verkoop binnendienst). Rust-Oleum Europe houdt zich het recht voor om de eigenschappen van haar producten te wijzigen zonder voorafgaande kennisgeving.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu