

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® MULTI-SURFACE



For direct application to many surfaces

- Direct to surface
- Paint & primer in one
- Quick drying
- Interior and exterior

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® MULTI-SURFACE

BESKRIVELSE

Rust-Oleum® CombiColor® Multi-Surface 7300 coating is a solvent based primer and topcoat in one, based on a modified Alkyd binder, providing good adhesion to many types of substrates. The product is lead- and chromate free.

ANBEFALET BRUG

Rust-Oleum CombiColor Multi-Surface 7300 can be applied on many different substrates like wood, metal, mdf, masonry, tiles, most rigid plastics, old concrete and more. We advise to do a small adhesion test prior to the application of the full surface. CombiColor Multi-Surface is intended for brush and roller application. For metal structures in a more aggressive industrial environment we advise CombiColor Original in combination with Rust-Oleum CombiPrimer Anti-Corrosion 3369/3380.

TEKNISK DATA

Tæthed:	1.0-1.6 kg/l
Glansgrad:	Blank,Mat,Satin
Glansgrad ved 60°:	60° GLOSS:> 80% SATIN:25-35% MATT: <10%
Faststofindhold i vægt:	GLOSS: 65± 2% SATIN: 76±2% MATT: 77±2%
Varmebestandighed:	80°C (dry heat), at elevated temperatures discoloration may occur.

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	4 hours (20°C), 6 hours (10°C), 2 hours (30°C)
Håndteringstør:	8 hours (20°C), 16 hours (10°C), 6 hours (30°C)
Genbehandlingstør:	16 hours (20°C), 24 hours (10°C), 8 hours (30°C)
Fuldt hærdet:	7 days (20°C), 14 days (10°C), 5 days (30°C)

ANBEFALET VÅDFILMTYKKELSE

105 µm

ANBEFALET TØRFILMTYKKELSE

62 µm

TEORETISK FORBRUG

9 - 10 m²/l at 62 µm dry per coat, depending on colour.

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Remove oil, grease and all other surface contaminations by alkaline cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping, wire brushing or sanding. Sand intact coatings to roughen the surface slightly. Test before application the compatibility with the old coating. The surface must be clean and dry during application. New galvanised (bright aluminium-like finish), Zinc and Aluminium (new and old) surfaces have to be primed first with CombiPrimer 3302. Aged galvanised (matt grey appearance, showing white rust) should first be cleaned with an acid cleaner (e.g. Rust-Oleum® SE108) or by mechanical abrasion with for example ScotchBrite. Very porous surfaces should be sealed prior to application of CombiColor® Multi-Surface.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Temperature of air, substrate and coating material between 5° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING OG FORTYNDING: PENSEL

Use natural bristles, long hair brushes. Thinning generally not required

PÅFØRING OG FORTYNDING: RULLE

Use short nap, poly-amid 6-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness Thinning generally not required.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Not recommended.

RENGØRING AF UDSKYR/SPILD

Use Rust-Oleum Thinner 160.

SIKKERHEDSDATA

VOC-niveau:	350 g/l
VOC-færdigblanding:	350 g/l
VOC-kategori:	A/i
VOC-grænse:	500 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 20/03/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu