

RUST-OLEUM®
— INDUSTRIAL —



COMBICOLOR® NON ZINC PRIMER



High quality primer for CombiColor® Non Zinc

- Recoatable after 2 hours
- For new / slightly rusted surfaces
- Grey for light coloured topcoats
- Red for dark coloured topcoats

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® NON ZINC PRIMER

BESKRIVELSE

RUST-OLEUM® CombiColor Non Zinc Primer 3369ZF Red / 3380ZF Grey are fast drying primers based on an aromatic free short oil alkyd resin. The product contains zinc-free rust-inhibitive pigments and is lead- and chromate free.

ANBEFALT BRUK

RUST-OLEUM CombiColor Non Zinc Primer should be used on new or prepared rusted steel surfaces to provide and enhance protection against corrosion. CombiColor Non Zinc Primer is primarily intended for brush application and can also be applied by roller and air spray. CombiColor Non Zinc Primer should be used in general industrial exposures, normal humidity and interior applications and should be recoated with CombiColor Non Zinc.

ANBEFALT SYSTEM

RUST-OLEUM CombiColor Non Zinc Primer / RUST-OLEUM CombiColor Non Zinc (Gloss or Satin)

TEKNISKE DATA

Tetthet:	1.21
Glansgrad:	Matt
Tørrstoffinnhold i volum:	44,8%
Varmebestandig:	120°C (dry heat)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 hour (20°C), 2 hours (10°C), ½ hours (30°C)
Håndterbar:	2 hour (20°C), 4 hours (10°C), 1 hour (30°C)
Overmalbar:	2 hours (20°C), 4 hours (10°C), 1 hour (30°C)
Herdetid:	7 days (20°C), 14 days (10°C), 5 days (30°C)

ANBEFALT VÅTFILMTYKKELSE

80 µm

ANBEFALT TØRRFILMTYKKELSE

35 µm

TEORETISK FORBRUK

12,8 m²/l at 35 µm dry

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 2/3 (ISO 8501-1 : 1988). Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING & FORTYNNING: PENSEL

Up to 10% volume RUST-OLEUM Thinner 7301. Use natural bristles, longhair brushes.

PÅFØRING & FORTYNNING: RULLE

Up to 10% volume RUST-OLEUM Thinner 7301. Use medium nap, 8-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

10-20% volume RUST-OLEUM Thinner 7301. Gravity cup and pressure cup. Tip size: 1.2 - 1.8 mm. Atomizing pressure: 2 - 4 bar.

RENGJØRING AV UTSTYR/SPILL

Use RUST-OLEUM Thinner 7301 or white spirit.

MERKNADER

Maximum dry film thickness per coat: 60 µm dry, equals 135 µm wet.

SIKKERHETSDATA

VOC ferdigblandet:	497 g/l
VOC kategori:	A/i
VOC grense:	500 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 13/05/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu