

RUST-OLEUM®
INDUSTRIAL



COMBICOLOR® HAMMERTONE AEROSOL

One coat system for metal protection, direct to rust

- Lead- and chromate-free
- Contains rust-inhibitive pigments for additional corrosion protection
- Excellent hiding properties
- High gloss appearance

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® HAMMERTONE AEROSOL

DESCRIPTION

RUST-OLEUM® CombiColor Aerosols Hammertone 7300 are based on a urethane modified alkyd.

DOPORUČENÉ POUŽITÍ

RUST-OLEUM CombiColor Aerosols Hammertone 7300 can be applied directly on bare, manually derusted or with CombiPrimer Anti-Corrosion 3369/3380 primed steel. RUST-OLEUM CombiColor Aerosols Hammertone 7300 are intended for small maintenance jobs or for touch-up. RUST-OLEUM CombiColor Aerosols Hammertone 7300 should be used in light industrial exposures, normal humidity and interior applications.

TECHNICAL DATA

Hustota (g/cm ³):	1.0 kg/l
Úroveň lesku:	Gloss
Obsah pevných látek v objemu:	41.5%
Tepelná odolnost:	90°C

DRY TIMES BY 20° C/RH 50%

Suché na manipulaci:	4 hours
Suchý nátěr:	2 hours
Plně vytvrzené:	7 days

TEORETICKÁ SPOTŘEBA

2 - 3 m² per spray can (400 ml).

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with CombiPrimer Tack Coat 3302.

NÁVOD K POUŽITÍ

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

PODMÍNKY POUŽITÍ

For optimum results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Up to 10 vol. % with 7301. Use natural bristles, long hair flat brushes for optimal hammertone appearance.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Up to 10 vol. % with 7301. Use short nap poly-amide (Perlon 6 - 12 mm) rollers.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

10-25 vol.% Rust-Oleum Thinner 7302. Gravity cup and pressure cup. Tip size: 1.0 - 1.5 mm. Atomising pressure 2 - 4 bar.

POZNÁMKY

Prevent application of too thick layers because this can cause problems with drying and sagging.

SAFETY DATA

VOC readymix:	495 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	500 g/l
Grenelle:	C
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 20/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu