

RUST-OLEUM®
INDUSTRIAL



COMBICOLOR® HAMMERTONE AEROSOL

One coat system for metal protection, direct to rust

- Lead- and chromate-free
- Contains rust-inhibitive pigments for additional corrosion protection
- Excellent hiding properties
- High gloss appearance

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® HAMMERTONE AEROSOL

BESKRIVELSE

RUST-OLEUM® CombiColor Aerosols Hammertone 7300 are based on a urethane modified alkylid.

ANBEFALET BRUG

RUST-OLEUM CombiColor Aerosols Hammertone 7300 can be applied directly on bare, manually derusted or with CombiPrimer Anti-Corrosion 3369/3380 primed steel. RUST-OLEUM CombiColor Aerosols Hammertone 7300 are intended for small maintenance jobs or for touch-up. RUST-OLEUM CombiColor Aerosols Hammertone 7300 should be used in light industrial exposures, normal humidity and interior applications.

TEKNISK DATA

Tæthed:	1.0 kg/l
Glansgrad:	Blank
Tørstofindhold i volumen:	41.5%
Varmebestandighed:	90°C

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Håndteringstør:	4 hours
Genbehandlingstør:	2 hours
Fuldt hærdet:	7 days

TEORETISK FORBRUG

2 - 3 m² per spray can (400 ml).

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Prime or spot prime with the recommended RUST-OLEUM Primers. Sand intact coatings to provide a proper key for adhesion. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with CombiPrimer Tack Coat 3302.

BRUGSANVISNING

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

ANVENDELSESBETINGELSER

For optimum results the relative humidity shall be below 85% and the temperature of the can and substrate above 10°C.

PÅFØRING OG FORTYNDING: PENSEL

Up to 10 vol. % with 7301. Use natural bristles, long hair flat brushes for optimal hammertone appearance.

PÅFØRING OG FORTYNDING: RULLE

Up to 10 vol. % with 7301. Use short nap poly-amide (Perlon 6 - 12 mm) rollers.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

10-25 vol.% Rust-Oleum Thinner 7302. Gravity cup and pressure cup. Tip size: 1.0 - 1.5 mm. Atomising pressure 2 - 4 bar.

BEMÆRKNINGER

Prevent application of too thick layers because this can cause problems with drying and sagging.

SIKKERHEDSDATA

VOC-færdigblanding:	495 g/l
VOC-kategori:	A/i
VOC-grænse:	500 g/l
grenelle:	c
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 20/03/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu