



# **COATING PRT®**

# Flexible, long lasting finish for roofs or walls

- · Flexible durable paint for renovation of roofs, ideal for making roofs white
- · Resistant to UV, acid rain, heat, frost and pollution
- Ideal topcoat for DACFILL® or NOXYDE® to reduce dirt pickup
- · Can be used in high humidity areas
- · Can also be used on walls

# KNOW-HOW TO PROTECT™

# **COATING PRT®**

## DESCRIPTION

Single pack high performace topcoat for walls and roofs, ideal for moist conditions and making roofs white. Also ideal to minimise dirt retention on DACFILL® or NOXYDE®.

## RECOMMENDED USE

- Coating of inner and outer walls that can be exposed to high humidity, f.i. bathrooms, kitchens. etc.
- Topcoat on Dacfill (improved resistance against stagnating water and less dirt retention)
   or on Noxyde (less dirt retention)

## **TECHNICAL DATA**

Density (g/cm³): 1,12
Gloss Level: Satin
Solids Content in weight: 48%
Solids content in volume: 42%

Test data: SRI value for Coating PRT white after 4000 hours

weathering following ISO 16474-3:2020 : 98,2

(requirement: minimum 90)

# DRY TIMES BY 20° C/RH 50%

Touch dry: 3 hours
Dry to handle: 4 hours
Dry to recoat: 24 hours
Fully cured: 24 hours

# RECOMMENDED WET FILM THICKNESS

140 µm

# RECOMMENDED DRY FILM THICKNESS

60 um

## THEORETICAL CONSUMPTION

7 m²/l

# PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

If the product is applied directly on bitumen felt, the consumption can be considerably higher. Account must be taken of 3.5 m $^2$  / I. Apply a test patch before starting the works in order to determine the actual practical consumption.

# SURFACE PREPARATION

Clean the substrate. Allow to dry, any previous coatings must be completely dry.

# **DIRECTIONS FOR USE**

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

# **APPLICATION CONDITIONS**

Work in a dry and well-ventilated area.

# **APPLICATION & THINNING: BRUSH**

All types.

## **APPLICATION & THINNING: ROLLER**

Short nap-mohair roller.

## **APPLICATION & THINNING: AIRLESS SPRAY**

Nozzle: 4/15 - Pressure: 100 bars.

# **APPLICATION & THINNING: AIR-ATOMISED SPRAY**

Do not dilute.

## **CLEANING OF EQUIPMENT / SPILLS**

Thinner 22 or white spirit.

#### REMARKS

Reversible paint system, this means that the product dissolves in its own solvent. Can be applied on new concrete.

## **SAFETY DATA**

 VOC level:
 481 g/l

 VOC readymix:
 499 g/l

 VOC category:
 A/i

 VOC limit:
 500 g/l

 Grenelle:
 Exterior

Remarks regarding safety: Consult Safety Data Sheet and Safety Information

printed on the can.

# **SHELF LIFE**

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Date issued:** 28/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V. Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T:+31 (0) 165 593 636 F:+31 (0) 165 593 600 Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147

38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

