

RUST-OLEUM®
INDUSTRIAL



COATING PRT®

Flexible, long lasting finish for roofs or walls

- Flexible durable paint for renovation of roofs, ideal for making roofs white
- Resistant to UV, acid rain, heat, frost and pollution
- Ideal topcoat for DACFILL® or NOXYDE® to reduce dirt pickup
- Can be used in high humidity areas
- Can also be used on walls

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COATING PRT®

DESCRIPTION

Single pack high performance topcoat for walls and roofs, ideal for moist conditions and making roofs white. Also ideal to minimise dirt retention on DACFILL® or NOXYDE®.

RECOMMENDED USE

- Coating of inner and outer walls that can be exposed to high humidity, f.i. bathrooms, kitchens, etc.
- Topcoat on Dacfill (improved resistance against stagnating water and less dirt retention) or on Noxyde (less dirt retention)

TECHNICAL DATA

Density (g/cm ³):	1,12
Gloss Level:	Satin
Solids Content in weight:	48%
Solids content in volume:	42%
Test data:	SRI value for Coating PRT white after 4000 hours weathering following ISO 16474-3:2020 : 98,2 (requirement: minimum 90)

DRY TIMES BY 20° C/RH 50%

Touch dry:	3 hours
Dry to handle:	4 hours
Dry to recoat:	24 hours
Fully cured:	24 hours

RECOMMENDED WET FILM THICKNESS

140 µm

RECOMMENDED DRY FILM THICKNESS

60 µm

THEORETICAL CONSUMPTION

7 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

If the product is applied directly on bitumen felt, the consumption can be considerably higher. Account must be taken of 3.5 m² / l. Apply a test patch before starting the works in order to determine the actual practical consumption.

SURFACE PREPARATION

Clean the substrate. Allow to dry, any previous coatings must be completely dry.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Work in a dry and well-ventilated area.

APPLICATION & THINNING: BRUSH

All types.

APPLICATION & THINNING: ROLLER

Short nap-mohair roller.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 4/15 - Pressure: 100 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Do not dilute.

CLEANING OF EQUIPMENT / SPILLS

Thinner 22 or white spirit.

REMARKS

Reversible paint system, this means that the product dissolves in its own solvent. Can be applied on new concrete.

SAFETY DATA

VOC level:	481 g/l
VOC readymix:	499 g/l
VOC category:	A/i
VOC limit:	500 g/l
Grenelle:	Exterior
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 13/05/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu