

RUST-OLEUM®
INDUSTRIAL



COATING PRT®

Flexible, long lasting finish for roofs or walls

- Flexible durable paint for renovation of roofs, ideal for making roofs white
- Resistant to UV, acid rain, heat, frost and pollution
- Ideal topcoat for DACFILL® or NOXYDE® to reduce dirt pickup
- Can be used in high humidity areas
- Can also be used on walls

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COATING PRT®

BESKRIVELSE

Single pack high performance topcoat for walls and roofs, ideal for moist conditions and making roofs white. Also ideal to minimise dirt retention on DACFILL® or NOXYDE®.

ANBEFALT BRUK

- Coating of inner and outer walls that can be exposed to high humidity, f.i. bathrooms, kitchens, etc.
- Topcoat on Dacfill (improved resistance against stagnating water and less dirt retention) or on Noxyde (less dirt retention)

TEKNISKE DATA

Tetthet:	1,12
Glansgrad:	Satinert
Tørrstoffinnhold i vekt:	48%
Tørrstoffinnhold i volum:	42%
Testdata:	SRI value for Coating PRT white after 4000 hours weathering following ISO 16474-3:2020 : 98,2 (requirement: minimum 90)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtør:	3 hours
Håndterbar:	4 hours
Overmalbar:	24 hours
Herdetid:	24 hours

ANBEFALT VÅTFILMYKKELSE

140 µm

ANBEFALT TØRRFILMYKKELSE

60 µm

TEORETISK FORBRUK

7 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

If the product is applied directly on bitumen felt, the consumption can be considerably higher. Account must be taken of 3.5 m² / l. Apply a test patch before starting the works in order to determine the actual practical consumption.

KLARGJØRING AV OVERFLATE

Clean the substrate. Allow to dry, any previous coatings must be completely dry.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Work in a dry and well-ventilated area.

PÅFØRING & FORTYNNING: PENSEL

All types.

PÅFØRING & FORTYNNING: RULLE

Short nap-mohair roller.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 4/15 - Pressure: 100 bars.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Do not dilute.

RENGJØRING AV UTSTYR/SPILL

Thinner 22 or white spirit.

MERKNADER

Reversible paint system, this means that the product dissolves in its own solvent. Can be applied on new concrete.

SIKKERHETSDATA

VOC nivå:	481 g/l
VOC ferdigblandet:	499 g/l
VOC kategori:	A/i
VOC grense:	500 g/l
grenelle:	exterior
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 13/05/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu