

RUST-OLEUM®
INDUSTRIAL

COMBICOLOR® ORIGINAL Transparent

1-coat system for metal protection, direct to rust.



- Transparent anti-rust varnish
- Primer and topcoat in one
- For application onto rust, bare metal
- High coverage: 10 m² per liter
- Sag resistant, no brush strokes

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ORIGINAL Transparent

BESKRIVELSE

CombiColor® Original Transparent 7310 coating is primer and topcoat in one, based on a fast drying short oil alkyd, providing good drying properties at low temperatures. The product contains a non-zinc rust-inhibitive pigment and is lead- and chromate free. Product is transparent and can be used as an anti-rust varnish.

ANBEFALT BRUK

CombiColor® Original Transparent 7310 should be applied on bare or manually derusted steel. CombiColor® Original Transparent is intended for brush and roller application and can also be applied by air spray. CombiColor® Original Transparent 7310 offers corrosion protection in a light industrial environment.

TEKNISKE DATA

Densitet:	1;01
Glansgrad:	Blank
Glansgrad ved 60°:	Gloss:90%
Tørrestoffinnhold i vekt:	50 ± 1 %
Tørrestoffinnhold i volum:	42± 1 %.
Varmebestandig:	90°C (dry heat), at elevated temperatures discoloration may occur.

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 hour (20°C), 1 ½ hours (10°C), 3/4 hour (30°C)
Håndterbar:	4 hours (20°C), 8 hours (10°C), 3 hours (30°C)
Tørketid:	4 hours (20°C), 8 hours (10°C), 3 hours (30°C)
Fullt herdet:	5 days (20°C), 7days (10°C), 4 days (30°C)

ANBEFALT VÅTFILMTRYKKEELSE

100 µm @ 10m²/L

ANBEFALT TØRRFILMTRYKKEELSE

42µm

FORBRUK

10 m²/l at 42 µm dry

FORBRUK INFORMASJON

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEREDELSE

Remove oil, grease and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 3 (ISO 8501-1 : 1988), light blast cleaning or sanding. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

PÅFØRING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Temperature of air, substrate and coating material between 5° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING & FORTYNNING: PENSEL

Use natural bristles, long hair brushes.

PÅFØRING & FORTYNNING: RULLE

Use short nap, polyamide 6-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Gravity cup and pressure cup. Tip size: 1.0 -1.5 mm. Atomising pressure: 2 - 4 bar.

RENGJØRING AV REDSKAP/SØL

Use RUST-OLEUM Thinner 7301 or RUST-OLEUM Thinner 160.

INFORMASJON

Maximum dry film thickness per coat: 55 µm dry, equals 131 µm wet.

SIKKERHETSDATA

VOC nivå:	499 g/l
VOC ferdigblandet:	477 g/l
VOC kategori:	A/i
VOC grense:	500 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 22/06/2026

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Forbehold: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu