

**RUST-OLEUM**<sup>®</sup>  
INDUSTRIAL

## COMBICOLOR<sup>®</sup> ORIGINAL Transparent

# 1-coat system for metal protection, direct to rust.



- Transparent anti-rust varnish
- Primer and topcoat in one
- For application onto rust, bare metal
- High coverage: 10 m<sup>2</sup> per liter
- Sag resistant, no brush strokes

KNOW-HOW TO PROTECT<sup>™</sup>

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# COMBICOLOR® ORIGINAL Transparent

## BESKRIVNING

CombiColor® Original Transparent 7310 coating is primer and topcoat in one, based on a fast drying short oil alkyd, providing good drying properties at low temperatures. The product contains a non-zinc rust-inhibitive pigment and is lead- and chromate free. Product is transparent and can be used as an anti-rust varnish.

## REKOMMENDERAD ANVÄNDNING

CombiColor® Original Transparent 7310 should be applied on bare or manually derusted steel. CombiColor® Original Transparent is intended for brush and roller application and can also be applied by air spray. CombiColor® Original Transparent 7310 offers corrosion protection in a light industrial environment.

## TEKNISK DATA

Densitet:	1;01
Glansnivå:	Glans
Glansnivå vid 60°:	Gloss:90%
Torrsubstansvikt:	50 ± 1 %
Torrsubstansvolym:	42± 1 %.
Värmebeständighet:	90°C (dry heat), at elevated temperatures discoloration may occur.

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour (20°C), 1 ½ hours (10°C), 3/4 hour (30°C)
Hanteringstorr:	4 hours (20°C), 8 hours (10°C), 3 hours (30°C)
Torktid:	4 hours (20°C), 8 hours (10°C), 3 hours (30°C)
Fullt härdad:	5 days (20°C), 7days (10°C), 4 days (30°C)

## REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm @ 10m²/L

## REKOMMENDERAD TORRFILMSTJOCKLEK

42µm

## ÅTGÅNG

10 m²/l at 42 µm dry

## ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FÖRBEREDELSE

Remove oil, grease and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 3 (ISO 8501-1 : 1988), light blast cleaning or sanding. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

## APPLICERING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICERINGSFÖRHÅLLANDEN

Temperature of air, substrate and coating material between 5° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## REDSKAP

Use natural bristles, long hair brushes.

## APPLICERING OCH SPÄDNING: ROLLER

Use short nap, polyamide 6-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness

## APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Gravity cup and pressure cup. Tip size: 1.0 -1.5 mm. Atomising pressure: 2 - 4 bar.

## RENGÖRING AV REDSKAP/SPILL

Use RUST-OLEUM Thinner 7301 or RUST-OLEUM Thinner 160.

## INFORMATION

Maximum dry film thickness per coat: 55 µm dry, equals 131 µm wet.

## SÄKERHETSDATA

VOC-nivå:	499 g/l
VOC färdigmix:	477 g/l
VOC-kategori:	A/i
VOC-gräns:	500 g/l
Anmärkingar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 22/06/2026

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu