

RUST-OLEUM®
INDUSTRIAL

COMBICOLOR® ORIGINAL Transparent

1-coat system for metal protection, direct to rust.



- Transparent anti-rust varnish
- Primer and topcoat in one
- For application onto rust, bare metal
- High coverage: 10 m² per liter
- Sag resistant, no brush strokes

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

COMBICOLOR® ORIGINAL Transparent

ОПИСАНИЕ

CombiColor® Original Transparent 7310 coating is primer and topcoat in one, based on a fast drying short oil alkyd, providing good drying properties at low temperatures. The product contains a non-zinc rust-inhibitive pigment and is lead- and chromate free. Product is transparent and can be used as an anti-rust varnish.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

CombiColor® Original Transparent 7310 should be applied on bare or manually derusted steel. CombiColor® Original Transparent is intended for brush and roller application and can also be applied by air spray. CombiColor® Original Transparent 7310 offers corrosion protection in a light industrial environment.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1,01
Гланцово ниво:	Гланц
Гланцово ниво при 60°:	Gloss:90%
Съдържание на сухо вещество (по тегло):	50 ± 1 %
Съдържание на сухо вещество (по обем):	42± 1 %.
Топлинна устойчивост:	90°C (dry heat), at elevated temperatures discoloration may occur.

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	1 hour (20°C), 1 ½ hours (10°C), 3/4 hour (30°C)
Сух за употреба:	4 hours (20°C), 8 hours (10°C), 3 hours (30°C)
Готов за повторно нанасяне:	4 hours (20°C), 8 hours (10°C), 3 hours (30°C)
group_dry_40_full_cure:	5 days (20°C), 7 days (10°C), 4 days (30°C)

МОКЪР СЛОЙ

100 µm @ 10m²/L

СУХ СЛОЙ

42µm

РАЗХОДНА НОРМА

10 m²/l at 42 µm dry

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

Remove oil, grease and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 3 (ISO 8501-1 : 1988), light blast cleaning or sanding. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

НАЧИН НА УПОТРЕБА

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

УСЛОВИЯ ЗА НАНАСЯНЕ

Temperature of air, substrate and coating material between 5° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Use natural bristles, long hair brushes.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Use short nap, polyamide 6-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Gravity cup and pressure cup. Tip size: 1.0 -1.5 mm. Atomising pressure: 2 - 4 bar.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Use RUST-OLEUM Thinner 7301 or RUST-OLEUM Thinner 160.

ЗАБЕЛЕЖКИ

Maximum dry film thickness per coat: 55 µm dry, equals 131 µm wet.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	499 g/l
Готов за употреба ЛОС (VOC Readymix):	477 g/l
Категория ЛОС:	A/i
group_voc_40_limit:	500 g/l
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 31/03/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu