

**RUST-OLEUM®**  
— INDUSTRIAL —



## COMBICOLOR® ORIGINAL GLOSS



# One coat rust inhibitive system system for metal protection

- Primer and topcoat in one
- For application onto rust, bare metal
- High coverage: 10.3 m<sup>2</sup> per liter
- Sag resistant, no brush strokes
- Usable down to 5°C

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# COMBICOLOR® ORIGINAL GLOSS

## OMSCHRIJVING

CombiColor® Original Metal 7300/7400 coating is primer and topcoat in one, based on a urethane modified alkyd, providing good drying properties at low temperatures. The product contains rust-inhibitive pigments and is lead- and chromate free.

## AANBEVOLEN GEBRUIK

CombiColor® Original 7300/7400 should be applied on bare, manually derusted or with CombiColor® Anti-Corrosion Primer 3369/3380 primed steel. CombiColor® Original is intended for brush and roller application and can also be applied by air spray. CombiColor® Original 7300/7400 offers corrosion protection in a light industrial environment. For metal structures in a more aggressive industrial environment, prior application of a CombiColor® Anti-Corrosion Primer 3369/3380 is recommended.

## TECHNISCHE GEGEVENS

|                                |                                                                    |
|--------------------------------|--------------------------------------------------------------------|
| Dichtheid (g/cm³):             | 0.9-1.10 (Black - White)                                           |
| Glansgraad:                    | Hoogglans                                                          |
| Glansgraad bij 60°:            | 95%                                                                |
| Vaste stof gehalte in gewicht: | 62,5± 3%                                                           |
| Vaste stof gehalte in volume:  | 53-57%                                                             |
| Hittebestendigheid:            | 90°C (dry heat), at elevated temperatures discoloration may occur. |

## DROOGTIJDEN BIJ 20° C/RV 50%

|                     |                                                  |
|---------------------|--------------------------------------------------|
| Kleefvrij:          | 2 hours (20°C), 3 hours (10°C), 1 ½ hours (30°C) |
| Hanteerbaar:        | 8 hours (20°C), 16 hours (10°C), 6 hours (30°C)  |
| Overschilderbaar:   | 16 hours (20°C), 24 hours (10°C), 8 hours (30°C) |
| Volledig uitgehard: | 7 days (20°C), 14 days (10°C), 5 days (30°C)     |

## AANBEVOLEN NATTE LAAGDIKTE

100 µm

## AANBEVOLEN DROGE LAAGDIKTE

55 µm

## THEORETISCH VERBRUIK

10.3 m²/l at 55 µm dry, depending on colour.

## PRAKTISCH VERBRUIK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## ONDERGROND VOORBEHANDELING

Remove oil, grease and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 3 (ISO 8501-1 : 1988), light blast cleaning or sanding. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with CombiColor® Adhesion Primer 3302.

## INSTRUCTIES VOOR GEBRUIK

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATIEOMSTANDIGHEDEN

Temperature of air, substrate and coating material between 5° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## VERDUNNING & APPLICATIE: KWAST

Up to 10% volume CombiColor® Thinner 7301. Use natural bristles, long hair brushes.

## VERDUNNING & APPLICATIE: ROLLER

Up to 10% volume CombiColor® Thinner 7301. Use short nap, polyamide 6-12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness

## VERDUNNING & APPLICATIE: LUCHTSPUIT

10-25% volume CombiColor® Thinner 7301. Gravity cup and pressure cup. Tip size: 1.0 - 1.5 mm. Atomising pressure: 2 - 4 bar.

## REINIGEN VAN APPARATUUR / SPATTEN

Use CombiColor® Thinner 7301 or RUST-OLEUM Thinner 160.

## OPMERKINGEN

Maximum dry film thickness per coat: 75 µm dry, equals 135 µm wet. To avoid inhomogeneous appearance with aluminum colored coatings it is recommended to spray 7311 with HVLP. CombiColor® Original Metal 7300/7400 can be recoated with CombiColor® Aerosols 7300 within 4 hours or after 72 hours.

## VEILIGHEIDSGEGEVENS

|                             |                                                                      |
|-----------------------------|----------------------------------------------------------------------|
| VOC gehalte:                | 477 g/l                                                              |
| VOC readymix:               | 477 g/l                                                              |
| VOC categorie:              | A/i                                                                  |
| VOC limiet:                 | 500 g/l                                                              |
| Opmerkingen mbt veiligheid: | Consult Safety Data Sheet and Safety Information printed on the can. |
|                             | Gold version contains a separate Safety Data Sheet.                  |

## HOUDBAARHEID

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Uitgiftedatum: 19/02/2026

**Beschikbare kleuren en verpakkingsformaten:** Raadpleeg de betreffende productpagina op [www.rust-oleum.eu](http://www.rust-oleum.eu) voor een overzicht van de actueel beschikbare kleuren en verpakkingsgrootten.

**Disclaimer:** De informatie in dit document is naar ons beste weten juist en wordt te goeder trouw, maar zonder garantie gegeven. De gebruiker wordt geacht onafhankelijk de geschiktheid van onze producten voor zijn/haar eigen specifieke toepassing te testen. In geen geval is Rust-Oleum Europe aansprakelijk voor directe of indirecte schade. Producten dienen te worden opgeslagen, behandeld en aangebracht volgens de aanbevelingen van Rust-Oleum Europe op het productinformatieblad (technische fiche). Het is de verantwoordelijkheid van de gebruiker om altijd de laatste versie van het productinformatieblad (technische fiche) te raadplegen en te respecteren. Deze bladen zijn gratis te downloaden van de website [www.rust-oleum.eu](http://www.rust-oleum.eu) of op aanvraag bij de afdeling Customer Service (Verkoop binnendienst). Rust-Oleum Europe houdt zich het recht voor om de eigenschappen van haar producten te wijzigen zonder voorafgaande kennisgeving.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)