



## DAC HYDRO D

# High build decorative roof tile paint



- Higher layer thickness gives extra protection
- Resistant to UV radiation, acid rain, heat, frost and pollution
- Rain-proof after just 1 hour
- Smooth decorative finish with lasting colour and gloss retention
- Water-based formulation, low odour

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# DAC HYDRO D

## DESCRIPTION

Flexible and high build acrylic paint for renovation and protection of concrete or terracotta roof tiles.

## ODPORÚČANÉ POUŽITIE

Dac-Hydro-D renovates and protects in a durable way several kinds of roof coverings (concrete and terracotta roof tiles).

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,2
Úroveň lesku:	Satin
Obsah pevných látok v hmotnosti:	50%
Obsah pevných látok v objeme:	40%

## DRY TIMES BY 20° C/RH 50%

Na dotyk suché:	1 hour
Suché na manipuláciu:	2 hours
Suchý na opäťovné natieranie:	24 hours
Úplne vytvrdené:	1 week

## ODPORÚČANÁ HRÚBKA MOKRÉHO FILMU

170 µm

## ODPORÚČANÁ HRÚBKA SUCHÉHO FILMU

65 µm

## TEORETICKÁ SPOTREBA

6 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

After a good cleaning with pure water under high pressure (200 bars), all substrates have to be dry, clean, not chalking and normally absorbent (untreated roof tiles). For very closed substrates like varnished or enamelled tiles, an adhesion coat like Noxyde diluted with 25% water has to be foreseen. For all other substrates: corrugated asbestos cement sheets, concrete tiles of the Redland type and all weathered and / or very absorbent substrates, it is necessary to apply an adhesion coat in Primer 44HS. It is recommended to perform an adhesion test.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

> 8°C, relative humidity max. 80%.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted.

## APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Dilute with maximum 3% volume of water. Nozzle: 015 - 021 / Pressure: 160 - 220 bars.

## APLIKÁCIA A RIEDENIE: VZDUCHOVY ATOMIZOVANÝ SPREJ

Not recommended.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

## POZNÁMKY

Apply in 2 coats to avoid local gloss differences. It is not advisable to apply Dac-Hydro-D on artificial slates type "Eternit".

## SAFETY DATA

Úroveň VOC:	40 g/l
VOC readymix:	40 g/l
Kategória VOC:	A/i
Limit VOC:	140 g/l
Grenelle:	Exterior
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.