



## DAC HYDRO D

# High build decorative roof tile paint



- Higher layer thickness gives extra protection
- Resistant to UV radiation, acid rain, heat, frost and pollution
- Rain-proof after just 1 hour
- Smooth decorative finish with lasting colour and gloss retention
- Water-based formulation, low odour

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# DAC HYDRO D

## BESKRIVNING

Flexible and high build acrylic paint for renovation and protection of concrete or terracotta roof tiles.

## REKOMMENDERAD ANVÄNDNING

Dac-Hydro-D renovates and protects in a durable way several kinds of roof coverings (concrete and terracotta roof tiles).

## TEKNISK DATA

Densitet:	1,2
Glansnivå:	Satin
Torrsubstansvikt:	50%
Torrsubstansvolym:	40%

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour
Hanteringstorr:	2 hours
Torktid:	24 hours
Fultt härdad:	1 week

## REKOMMENDERAD VÅTFILMSTJOCKLEK

170 µm

## REKOMMENDERAD TORRFILMSTJOCKLEK

65 µm

## ÅTGÅNG

6 m<sup>2</sup>/l

## ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FÖRBEREDELSE

After a good cleaning with pure water under high pressure (200 bars), all substrates have to be dry, clean, not chalking and normally absorbent (untreated roof tiles). For very closed substrates like varnished or enamelled tiles, an adhesion coat like Noxyde diluted with 25% water has to be foreseen. For all other substrates: corrugated asbestos cement sheets, concrete tiles of the Redland type and all weathered and / or very absorbent substrates, it is necessary to apply an adhesion coat in Primer 44HS. It is recommended to perform an adhesion test.

## APPLICERING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICERINGSFÖRHÄLLANDE

> 8°C, relative humidity max. 80%.

## APPLICERING OCH SPÄDNING: PENSEL

Apply undiluted.

## APPLICERING OCH SPÄDNING: ROLLER

Apply undiluted.

## APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Dilute with maximum 3% volume of water. Nozzle: 015 - 021 / Pressure: 160 - 220 bars.

## APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Not recommended.

## RENGÖRING AV REDSKAP/SPILL

Water.

## INFORMATION

Apply in 2 coats to avoid local gloss differences. It is not advisable to apply Dac-Hydro-D on artificial slates type "Eternit".

## SÄKERHETSDATA

VOC-nivå:	40 g/l
VOC färdigmix:	40 g/l
VOC-kategori:	A/i
VOC-gräns:	140 g/l
grenelle:	exterior
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självläntigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.