

**RUST-OLEUM®**  
INDUSTRIAL



## DAC HYDRO PLUS

# Decorative and protective roof tile paint

- Quick, easy to apply and affordable
- No need for a special primer on concrete
- Cost effective coverage: 10m<sup>2</sup>/L
- Lasting gloss and colour
- Rain-proof after just 2 hours

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# DAC HYDRO PLUS

## DESCRIPTION

Flexible and durable acrylic paint for renovation and protection of concrete roof tiles.

## DOPORUČENÉ POUŽITÍ

Dac-Hydro-Plus renovates and protects in a durable way concrete and terracotta roof tiles.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,16
Úroveň lesku:	Satin
Obsah pevných látek v hmotnosti:	40%
Obsah pevných látek v objemu:	30%

## DRY TIMES BY 20° C/RH 50%

Dotykem suché:	1 hour
Suché na manipulaci:	2 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	1 week

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

1st coat: 110 µm (125 g/m<sup>2</sup>), 2nd coat: 85 µm (100 g/m<sup>2</sup>)

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

1st coat: 33 µm, 2nd coat: 26 µm

## TEORETICKÁ SPOTŘEBA

10 m<sup>2</sup>/l per coat

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

After a good cleaning with pure water under high pressure (200 bars), all substrates have to be dry, clean, not chalking and normally absorbent (untreated roof tiles). Apply an anti fungicidal solution such as AMW fungicidal Wash for removal of moss, etc. Recommended primers for substrate:

Concrete: no primer required

Eternit/fibre cement: use Dac Hydro Pro

Slate tiles: Primer 44HS or Pegafix

Terracotta tiles, concrete tiles type Redland, fully weathered and/or very porous: Primer 44HS

Very dense substrates: Noxyde diluted with 25% volume water

It is recommended to always perform an adhesion test.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

> 8°C, relative humidity max. 80%. Do not apply in full sun.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Dilute with maximum 3% volume of water. Nozzle: 009 - 013 / Pressure: 140 – 180 bars.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

## POZNÁMKY

Apply in 2 coats to avoid local gloss differences.

## SAFETY DATA

Úroveň těkavých organických

látek: 35 g/l

VOC readymix: 35 g/l

Kategorie VOC: A/i

Limitní hodnota VOC: 140 g/l

Grenelle: Exterior

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 13/05/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chiène  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu