

RUST-OLEUM®
INDUSTRIAL



DAC HYDRO PLUS

Decorative and protective roof tile paint

- Quick, easy to apply and affordable
- No need for a special primer on concrete
- Cost effective coverage: 10m²/L
- Lasting gloss and colour
- Rain-proof after just 2 hours

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

DAC HYDRO PLUS

BESKRIVNING

Flexible and durable acrylic paint for renovation and protection of concrete roof tiles.

REKOMMENDERAD ANVÄNDNING

Dac-Hydro-Plus renovates and protects in a durable way concrete and terracotta roof tiles.

TEKNISK DATA

Densitet:	1,16
Glansnivå:	Satin
Torrsubstansvikt:	40%
Torrsubstansvolym:	30%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour
Hanteringstorr:	2 hours
Torktid:	24 hours
Fullt härdad:	1 week

REKOMMENDERAD VÅTFILMSTJOCKLEK

1st coat: 110 µm (125 g/m²), 2nd coat: 85 µm (100 g/m²)

REKOMMENDERAD TORRFILMSTJOCKLEK

1st coat: 33 µm, 2nd coat: 26 µm

ÅTGÅNG

10 m²/l per coat

ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FÖRBEREDELSE

After a good cleaning with pure water under high pressure (200 bars), all substrates have to be dry, clean, not chalking and normally absorbent (untreated roof tiles). Apply an anti fungicidal solution such as AMW fungicidal Wash for removal of moss, etc. Recommended primers for substrate:

Concrete: no primer required

Eternit/fibre cement: use Dac Hydro Pro

Slate tiles: Primer 44HS or Pegafix

Terracotta tiles, concrete tiles type Redland, fully weathered and/or very porous: Primer 44HS

Very dense substrates: Noxyde diluted with 25% volume water

It is recommended to always perform an adhesion test.

APPLICERING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

> 8°C, relative humidity max. 80%. Do not apply in full sun.

REDSKAP

Apply undiluted

APPLICERING OCH SPÄDNING: ROLLER

Apply undiluted

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Dilute with maximum 3% volume of water. Nozzle: 009 - 013 / Pressure: 140 – 180 bars.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Not recommended

RENGÖRING AV REDSKAP/SPILL

Water.

INFORMATION

Apply in 2 coats to avoid local gloss differences.

SÄKERHETSDATA

VOC-nivå:	35 g/l
VOC färdigmix:	35 g/l
VOC-kategori:	A/i
VOC-gräns:	140 g/l
grenelle:	exterior
Anmärkingar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 13/05/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu