

Quality Paints since 1845
MATHYS[®]



DAC HYDRO PRO

Rapid curing paint for Eternit[®] roof tiles

- Perfect adhesion on tiles, even difficult surfaces like fibre cement
- Resistant to UV radiation, acid rain, heat, frost and pollution
- Can be recoated after just 4 hours
- Flexible elastic paint does not crack or peel
- Long lasting gloss and colour retention

DAC HYDRO PRO

DESCRIPTION

Rapid drying roof tile paint for fiber cement (Eternit®) tiles.

RECOMMENDED USE

Renovates and protects in a durable way concrete roof tiles and fibre cement roofing slates.

RECOMMENDED SYSTEM

Recommended primer per substrate:

- Concrete roofing tiles (normal porosity): No primer required
- Fibre cement (weathered and porous): Pegafix (see remarks)
- Fibre cement (dense, closed): No primer required
- Enamelled tiles: NOXYDE (25% diluted with water)

TECHNICAL DATA

Density (g/cm ³):	1,18
Gloss Level:	Satin
Solids content in volume:	42%

DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour
Dry to handle:	2 hours (rain proof)
Dry to recoat:	4 hours
Fully cured:	1 week

RECOMMENDED WET FILM THICKNESS

1st coat: 85 µm (100 g/m²), 2nd coat: 70 µm (80 g/m²)

RECOMMENDED DRY FILM THICKNESS

1st coat: 36 µm, 2nd coat: 29 µm

THEORETICAL CONSUMPTION

5 - 6 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

High pressure cleaning (120 – 150 kg/cm²) if necessary in combination with AMW Fungicidal Wash for removal of moss and algae. All substrates have to be dry, clean and sound before applying the coating system.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Application temperature between 15 - 35°C, relative humidity max. 80%. Do not apply in full sun. Maximum surface temperature: 35°C.

APPLICATION & THINNING: BRUSH

First coat dilute with 10-15% volume water; second coat dilute with maximum 5% volume water.

APPLICATION & THINNING: ROLLER

First coat dilute with 10-15% volume water; second coat dilute with maximum 5% volume water.

APPLICATION & THINNING: AIRLESS SPRAY

First coat dilute with 10-15% volume water; second coat dilute with maximum 5% water. Nozzle: 015 / Pressure: 140 – 180 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended

CLEANING OF EQUIPMENT / SPILLS

Water.

REMARKS

Apply in 2 coats to avoid local gloss differences. The surface must be dry, preferably no rain for 3 hours before applying the product. No dew or rain on the roof within 2 hours after application. Avoid spray applications when there are strong winds and provide cover for nearby substrates which do not need to be coated.

It is not recommended to apply Dac Hydro Pro on artificial slates of the Eternit type that are too strongly deteriorated. In order to verify, please check the mechanical stability of the surface after cleaning with a sharp knife or a screwdriver. If the fibres come loose, the surface can not be coated and needs to be renewed. It is recommended to always perform an adhesion test.

SAFETY DATA

VOC level:	39 g/l
VOC readymix:	39 g/l
VOC category:	A/i
VOC limit:	140 g/l
Grenelle:	Exterior
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 30°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu