

RUST-OLEUM®
INDUSTRIAL



DACFILL® FRIGO

Gas & vapour tight rubberlike coating

- Ideal for cold stores and storage rooms
- Resistance against sudden variations in temperature
- Does not contain solvents or bituminous products
- Flexible rubberlike coating is impact resistant
- Self-extinguishing (DIN 4102)

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

DACFILL® FRIGO

DESCRIPTION

Gas and vapour tight abrasion resistant rubberlike coating for walls and ceilings in e.g. cold stores.

DOPORUČENÉ POUŽITÍ

Gas and vapour tight coating for walls and ceilings, for example in cold stores.

TECHNICAL DATA

Hustota (g/cm ³):	1,48
Úroveň lesku:	Matt
Obsah pevných látek v hmotnosti:	70%
Obsah pevných látek v objemu:	55%

DRY TIMES BY 20° C/RH 50%

Dotykem suché:	1,5 hours
Suché na manipulaci:	4 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

680 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

380 µm

TEORETICKÁ SPOTŘEBA

Repainting existing gas-tight cells: 0,5 - 1 kg/m².
For making cells gas-tight: 2 - 3 kg/m² in two or more coats.

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

Clean the substrate. Dacfill-Frigo can be applied on:

1. Directly on insulation material such as polystyrene foam, polyurethane and other
2. With an adhesion layer, on concrete, bricks, wood, zinc, aluminium, etc.

On very porous substrates, e.g. cellular concrete: apply first an impregnating coat of Pegafix or Primer 44HS.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Minimum 5°C / maximum 85% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 018 - 026 / Pressure: 220 bars.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

POZNÁMKY

Water vapour diffusion resistance: $\mu = 26000$. Shore hardness A: > 45 . Oxygen permeability: 236 mg O₂/m² per day (DFT: 400 µm)

SAFETY DATA

Úroveň těkavých organických látek:	35 g/l
VOC readymix:	35 g/l
Kategorie VOC:	A/1
Limitní hodnota VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and the safety information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 10/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu