

RUST-OLEUM®
INDUSTRIAL



DACFILL® FRIGO

Gas & vapour tight rubberlike coating

- Ideal for cold stores and storage rooms
- Resistance against sudden variations in temperature
- Does not contain solvents or bituminous products
- Flexible rubberlike coating is impact resistant
- Self-extinguishing (DIN 4102)

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

DACFILL® FRIGO

DESCRIPTION

Gas and vapour tight abrasion resistant rubberlike coating for walls and ceilings in e.g. cold stores.

RECOMMENDED USE

Gas and vapour tight coating for walls and ceilings, for example in cold stores.

TECHNICAL DATA

Density (g/cm ³):	1,48
Gloss Level:	Matt
Solids Content in weight:	70%
Solids content in volume:	55%

DRY TIMES BY 20° C/RH 50%

Touch dry:	1,5 hours
Dry to handle:	4 hours
Dry to recoat:	24 hours
Fully cured:	1 week

RECOMMENDED WET FILM THICKNESS

680 µm

RECOMMENDED DRY FILM THICKNESS

380 µm

THEORETICAL CONSUMPTION

Repainting existing gas-tight cells: 0,5 - 1 kg/m².

For making cells gas-tight: 2 - 3 kg/m² in two or more coats.

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Clean the substrate. Dacfill-Frigo can be applied on:

1. Directly on insulation material such as polystyrene foam, polyurethane and other
2. With an adhesion layer, on concrete, bricks, wood, zinc, aluminium, etc.

On very porous substrates, e.g. cellular concrete: apply first an impregnating coat of Pegafix or Primer 44HS.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Minimum 5°C / maximum 85% R.H.

APPLICATION & THINNING: BRUSH

Apply undiluted.

APPLICATION & THINNING: ROLLER

Apply undiluted.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 018 - 026 / Pressure: 220 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended.

CLEANING OF EQUIPMENT / SPILLS

Water.

REMARKS

Water vapour diffusion resistance: $\mu = 26000$. Shore hardness A: > 45. Oxygen permeability: 236 mg O₂/m² per day (DFT: 400 µm)

SAFETY DATA

VOC level:	35 g/l
VOC ready mix:	35 g/l
VOC category:	A/i
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and the safety information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 10/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu