

RUST-OLEUM®
INDUSTRIAL



DACFILL® HZ



Durable waterproofing for horizontal roofs

- Quick drying 100% watertight coating
- Resistant to UV radiation, acid rain, heat, frost and pollution
- White colour reflects most sunlight
- Non-flammable and self-extinguishing
- Seamless elastic finish lasts for years

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

ОПИСАНИЕ

Quick drying watertight water-based liquid membrane for roofs. Forms a lasting elastic coat without joint or seams on horizontal roofs.

ПРЕПОРЪЧАНА УПОТРЕБА

Waterproofing protection of flat roofs. Also applicable in situations where quick water resistance or recoatability is required. Builds an abrasion resistant rubberlike coat without joints or seams, which is hardly flammable and self-extinguishing.

ТЕХНИЧЕСКИ ДАННИ

Пълтност (г/см ³):	1,25
Гланцово ниво:	matt
Съдържание на твърди частици в тегло:	62%
Съдържание на твърди вещества в обема:	51%
Пропускливост на водни пари:	$\mu = 1934$ (2 x 500 g/m ²)
Степен на смесване:	Base : Activator = 19.2 : 0.8 (Weight)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	1,5 hours
Сух за употреба:	1,5 hours
Готов за повторно нанасяне:	12 hours
Напълно втвърден:	1 week
Живот в гърне:	18 hours

МОКЪР СЛОЙ

1200 micron per coat (cons.: 1,5 kg/m²)

СУХ СЛОЙ

600 micron per coat (cons.: 1,5 kg/m²)

РАЗХОДНА НОРМА

Per coat: 1 - 1,5 kg/m² (depending of the substrate). To be applied in 2 coats.

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be well clean and dry, free from flakes, gravel, dust and dirt. Fill up joints with Elastofill, bridge active cracks with "Dacfill bridging mesh" and apply one of the following priming coats:

- On porous concrete, hard PVC and polyester: Primer 44HS
- On very smooth concrete: Noxyde diluted with 25% volume water
- On iron and steel: undiluted Noxyde

Roofing or bituminous materials over 1 year old can be coated directly with Dacfill HZ depending on its condition. To ensure optimal adhesion it is recommended to fixate the substrate with Parafix. Zinc, galvanised steel, copper, lead and aluminium can be recoated with Dacfill HZ, if required, after degreasing and slight sanding.

НАЧИН НА УПОТРЕБА

To ensure homogeneity, coating materials should be thoroughly stirred prior to use. Add B-component to the A-component while stirring mechanically. It is advised to use the mixed material during the same day. Unroll the Dacfill-mesh on the dry and clean substrate and fix it to the substrate with a first coat of Dacfill HZ (1 - 1,5 kg/m²) by roller. Mesh overlappings must be at least 5 cm. After drying, a second coat of Dacfill HZ is to be applied by roller or by airless so that the structure of the mesh is not visible anymore.

УСЛОВИЯ ЗА НАНАСЯНЕ

Dry weather: enough air ventilation (light breeze) or sunny conditions. Minimum Temperature: 5°C. Max. Relative humidity: 85%.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Square brush. Do not dilute.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Roller with long hairs (long nap). Do not dilute.

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Nozzle: 18 - 23 / Pressure: 220 bars. Do not dilute.

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Not advised

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water

ЗАБЕЛЕЖКИ

Dacfill-mesh must be used on every roof with a slope < 5%, in case of water stagnation and when movements of the substrates can be expected or can be feared (for more information about the application of the Dacfill-mesh, please consult our Technical Service). For substrates other than those mentioned above contact Technical Service Do NOT apply on TPO's (Thermoplastic Olefins i.e. Derbigum)

Drying times depend strongly on temperature, relative humidity and air movement. Surface drying (1 kg/m²): 30 minutes (high t° / low R.H.) , 6 hours (low t° / high R.H. / no wind) Shore hardness A (ASTM D 2240): 75

ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	55 g/l
Готов за употреба ЛОС (VOC Readymix):	55 g/l
Категория ЛОС:	A/j
Ограничение за ЛОС:	140 g/l
grenelle:	exterior
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоително в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случаин щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shandon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
36, av du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu